Low Charging Clear Zipper Overall Width (OW) STATSHIELD® ESD Shielding Bag Contents Metal In Construction Static Sancitive Handling Precautions Required Length (L) Made in America (PQ) Lead-free RoHS compliant Bag Date & Lot Code Printed for QC Traceablility Weld Weld

Side Weld Seals 3/8 in. (±0.10)



Specifications:

Standard Document

ANSI/ESD S541 (ANSI/ESD S20.20) ANSI/ESD S11.4

Electrical Properties

Surface Resistance: Outer Surface Inner Surface Discharge Shielding Charge Generation

Capacitance Probe (to dissipate 1 KV)

Typical Values

 1×10^4 to $< 1 \times 10^{11}$ ohms $1 \times 10^4 \text{ to} < 1 \times 10^{11} \text{ ohms}$ <20 nJ

Teflon: 0.09 nC/sq. in. Quartz: 0.01 nC/sq. in.

<30 volts

ANSI/ESD STM11.11

ANSI/ESD STM11.11 ANSI/ESD STM11.31, EIA 541 Modified Incline Plane

Meets Requirements of:

ESD Protective Packaging

Test Procedures/Method

Level 3 Technical Requirements

Modified Incline Plane

ANSI/EIA-541/Appendix E, 1kV Discharge

Physical Properties

Film Thickness Width (Inside Dimensions) Length (Inside Dimensions) Light Transmission Heat Seal Tensile Strength Puncture Resistance Silicone

Nominal -0" / + 0.125" Nominal ± 0.125" >40% (Tobias) >10 lbs/in 4600 PSI, 32 MPa >10 lbs Not detected Marking Adhesion Pass

Nominal 0.0030" (0.0762mm) ±10% MIL-STD-3010, 1003

> **ASTM D-1003** 375°F, 1/2 sec 60 psi **ASTM 882**

MIL-STD-3010, 2065 FTIR

IPC-TM-650 2.4.1

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

RoHS 2, REACH and Conflict Minerals Statement

None of the RoHS 2 restricted materials, REACH substances of very high concern as of 2016/06/20, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Desco Industries Inc. Limited Warranty at Desco.com.

Low Charging Static

Low Charging Static

Dissipative Proprietary

Inner Polvethylene Laver

Dissipative Proprietary Outer Polyester Layer Aluminum Shielding Layer

Mixed Unsortable Plastic Scrap

Soft Fold Bottom

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Desco's bags are recyclable

Statshield® bags are packaged 100 per package in an oversized shielding bag. See Shielding Bag Storage at TB-7057.

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click HERE

Specifications and procedures subject to change without notice.



STATSHIELD® BAG. SHIELDING. METAL-IN CONSTRUCTION. ZIPPER. 0.0030" (0.0762mm)



DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407 PHONE (781) 821-8370

DRAWING NUMBER 13605

DATE: January 2017

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Desco: