

TECHNICAL DATA SHEET

Document number: TTDS-023

Issue: 4

Date: July 2007

TMS-SCE HEAT SHRINK SLEEVE

MATERIAL DESCRIPTION:	Thin wall flame retarded radiation cross-linked modified polyolefin heat-shrinkable tubing, assembled as organized cut sleeves in a "ladder" configuration. 3:1 and 2:1 shrink ratio products available.
USE:	Identification of wires and cables by computer-based printing onto sleeves. Sleeves can also provide terminal insulation and strain relief. Suitable for a wide variety of applications, including aerospace, military and rail applications.
PRINT METHOD/RIBBON:	Thermal transfer: Tyco T312M-PRINTER, Tyco TMS-RJS-RIBBON-4RPSCE (black), Tyco 1330-3102-10 (white) Thermal transfer: Tyco T200 Series, Tyco TMS-101-RIBBON-4RPSCE (black), Tyco TMS-101-RIBBON-WH-4SCE (white) Thermal transfer: Tyco T408M-PRINTER, Tyco TMS-RJS-RIBBON-4RPSCE Thermal transfer: QLS-2001, Tyco TMS-RJS-RIBBON-4RPSCE Dot matrix: Epson LQ870 printer, Tyco TMS-SYSTEM-SIX-RIBBON-A ribbon. Dot matrix: AM6310, Tyco 1892BK04-RIBBON
SERVICE TEMPERATURE:	-55°C to +135°C (-67°F to +275°F).
MAXIMUM STORAGE TEMPERATURE:	40°C (104°F).
COLORS:	White and yellow. Nine other colors available on request. TMS-SCE-2X sleeves meet the requirements of MIL-STD-104 Class 1.
SHELF LIFE	Sleeves meet the material and performance requirements of SAE-AMS-DTL-23053/5 Classes 1 & 3.

Page 1 of 3

Business locations:

 N America: + 1 650 361 3860 (West Coast)
 France: + 33 (0) 4 76 09 96 96 (Labels)
 Germany: + 49 (0) 6074 8908 0
 UK: + 44 (0) 1495 244 000 (Labels)
 Japan: + 81 (0) 44 900 5102

 N America: + 1 401 751 6505 (East Coast)
 France: + 33 (0) 1 34 20 21 22 (Other products)
 UK: + 44 (0) 1793 528171 (Other products)
 Singapore: + 65 (0) 4866 151

All the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.

TECHNICAL DATA SHEET

Document number: TTDS-023

Issue: 4

Date: July 2007

TMS-SCE HEAT SHRINK SLEEVE

AGENCY APPROVALS:	UL recognised Standard 224 (File E35586). CSA certified (File 31929).
TENSILE STRENGTH:	10.3MPa minimum (SAE-AMS-DTL-23053/5).
ULTIMATE ELONGATION:	200% minimum (SAE-AMS-DTL-23053/5).
2% SECANT MODULUS:	172.4MPa maximum (SAE-AMS-DTL-23053/5).
LONGITUDINAL CHANGE:	-20% maximum (-5% maximum for TMS-SCE-2X products) (SAE-AMS-DTL-23053/5).
HEAT AGEING:	100% UE retained and print legible after 168 hours at 175°C (347°F).
HEAT SHOCK:	No cracking, dripping or flowing and print legible after 4 hours at 250°C (482°F).
LOW TEMPERATURE FLEXIBILITY:	No cracking after 4 hours at -55°C (-67°F), 11mm (7/16 inch) mandrel bend.
MOLD GROWTH:	Print legible after 56 day incubation (ISO 846B)- tensile strength and ultimate elongation maintained after testing.
FLAMMABILITY:	TMS-SCE 2X is UL224-VW-1 rated. TMS-SCE is UL224-all tube flame test rated Burn time 60 seconds maximum (ASTM D2671 Procedure B). No flag burn; no burning of cotton or dripping (ASTM D2671 Procedure C).
WATER ABSORPTION:	0.5% maximum (ASTM D570). 19.7MV/m minimum (ASTM D2671).

Page 2 of 3

Business locations:

 N America: + 1 650 361 3860 (West Coast)
 France: + 33 (0) 4 76 09 96 96 (Labels)
 Germany: + 49 (0) 6074 8908 0
 UK: + 44 (0) 1495 244 000 (Labels)
 Japan: + 81 (0) 44 900 5102

 N America: + 1 401 751 6505 (East Coast)
 France: + 33 (0) 1 34 20 21 22 (Other products)
 UK: + 44 (0) 1793 528171 (Other products)
 Singapore: + 65 (0) 4866 151

All the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.

TECHNICAL DATA SHEET

Document number: TTDS-023

Issue: 4

Date: July 2007

TMS-SCE HEAT SHRINK SLEEVE

DIELECTRIC STRENGTH:

PRINT PERMANENCE:

Print legible after 50 rubs (SAE AS81531, 4.6.2).

Print legible after 30 strokes (MIL-STD-202F, method 215J).

FLUID RESISTANCE:

THREAT	TEST	EFFECT
MIL-L-7808 lubricating oil	24 hours at 24°C (75°F), SAE AS81531 4.6.2 (20 rubs)	Print legible
MIL-L-23699 lubricating oil	24 hours at 24°C (75°F), SAE AS81531 4.6.2 (20 rubs)	Print legible
MIL-H-5606 hydraulic fluid	24 hours at 24°C (75°F); SAE AS81531 4.6.2 (20 rubs)	Print legible
MIL-T-83133 aircraft fuel (JP-8)	24 hours at 24°C (75°F); SAE AS81531 4.6.2 (20 rubs)	Print legible
Aviation gasoline (100/130)	24 hours at 24°C (75°F); SAE AS81531 4.6.2 (20 rubs)	Print legible
Skydrol™ 500 hydraulic fluid	24 hours at 24°C (75°F); SAE AS81531 4.6.2 (20 rubs)	Print legible
5% salt water (A-A-694)	24 hours at 24°C (75°F), SAE AS81531 4.6.2 (20 rubs)	Print legible
MIL-A-8243 anti-icing fluid	24 hours at 24°C (75°F); SAE AS81531 4.6.2 (20 rubs)	Print legible

Notes: See Tyco specification RT 1805 for full TMS-SCE performance & dimensional details.

Some types of neoprene insulation used in jackets contain additives that can migrate to the surface and discolor the polyolefin TMS-SCE sleeves. Any discoloration is dependent on the composition of the neoprene, combined with application conditions. Users should independently evaluate the suitability of TMS-SCE sleeves for applications involving neoprene-jacketed cables.

Page 3 of 3

Business locations:

☎ N America: + 1 650 361 3860 (West Coast)
 ☎ France: + 33 (0) 4 76 09 96 96 (Labels)
 ☎ Germany: + 49 (0) 6074 8908 0
 ☎ UK: + 44 (0) 1495 244 000 (Labels)
 ☎ Japan: + 81 (0) 44 900 5102

☎ N America: + 1 401 751 6505 (East Coast)
 ☎ France: + 33 (0) 1 34 20 21 22 (Other products)
 ☎ UK: + 44 (0) 1793 528171 (Other products)
 ☎ Singapore: + 65 (0) 4866 151

All the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.