



- Water Repellent When Properly Sealed
- Will Not Support Growth Of Bacteria
- **Disinfects Easily**
- Adhesive Resists Most Cleaners And Disinfectants

Nominal Size	Part #	Wall Thickness	Bulk Box	Box 8x8	Box 6x6	Box 4x4	Available Colors	Lbs/ 10Pcs.
3/8"	L6N0.38	0.046"	250	90	50	30	2	0.9
1/2"	L6N0.50	0.046"	250	70	40	25	2	1.0
3/4"	L6N0.75	0.046"	125	50	30	15	2	1.8
1″	L6N1.00	0.046"	88	30	20	9	2	2.2
1 1/4"	L6N1.25	0.046"	63	20	10	6	2	2.6

4' Pcs. Put-Ups ——

Cut Cleanly Hot Knife

Material Laminated Polyester

Grade

L6N

NA

Monofilament Diameter


Stylish Fluid Protection For Wires & Cables

Our new L6 Liquid Wrap semi-rigid wraparound sleeving is engineered from tough braided polyester, and laminated with a layer of strong Mylar sheeting. This combination provides a strong and lightweight solution for any application that requires protection from repeated exposure to the elements.

The wraparound construction, with 12% edge overlap makes installation easy over existing assemblies or harnesses, and the extra wide adhesive strip ensures a positive, aggressive seal against damage from exposure.

L6 is available in 4' pre-cut sticks in Black or White.

L6 is ideal for marine and automotive wiring harnesses, and also for cable management in medical applications.



■¬ Colors Available:

2 = BK & WH










Abrasion Resistance High

Material Destroyed-Braid Worn Through in **Both Directions** 10,338 Test Cycles



CHEMICAL RESISTANCE

1=No Effect

4=More Affected

2=Little Effect

5=Severely Affected

3=Affected

PHYSICAL PROPERTIES

Aromatic Solvents	2
Aliphatic Solvents	
Chlorinated Solvents	
Weak Bases	1
Salts	1
Strong Bases	
Salt Water 0-S-1926	1
Hydraulic Fluid MIL-H-5606	1
Lube Oil <i>MIL-L-7808</i>	1
De-Icing Fluid MIL-A-8243	
Strong Acids	3
Strong Oxidants	
Esters/Ketones	1
UV Light	1
Petroleum	1
Fungus ASTM G-21	1
Halogen FreeY	'es
RoHSY	'es
SVHC No	ne

Monofilament Diameter ASTM D-204	NA
Flammability Rating FMVSS-302 Approved	
Recommended Cutting	Scissor
Colors	1
Wall Thickness	
Tensile Strength (Yarn) ASTM D-2256 Lbs	
Specific Gravity ASTM D-792 _	1.38
Moisture Absorption % ASTM D-570	12
Hard Vacuum Data ASTM E-595 at 10-5 torr	
TML	19
CVCM	.00
WVR	16
Smoke D-Max ASTM E-662	56
Outgassing	Med
Oxygen Index ASTM D-2863	21