3MTM Polyester Film Electrical Tape 56 with Thermosetting Rubber Adhesive

Data Sheet	January 20	014
------------	------------	-----

Description	3M Polyester Film Tape 56 is a 1-mil yellow polyester film with rubber thermosetting adhesive.
Applications	The 56 tape is especially suited for use as layer insulation and coil cover in 130° applications.
Agency Approvals	UL recognized component listing not to exceed 130°C (266°F), Product Category

Agency Approvals & Self Certifications

UL recognized component listing not to exceed 130°C (266°F), Product Category OANZ2, and 3M File No. E17385

UL File Number E17385 A and B, Guide OANZ2. Underwriters Laboratories (UL) recognized products have been evaluated for use as components of end-product equipment that is listed or classified by UL. To achieve Underwriters Laboratories recognition, component construction must meet UL specifications and conditions of acceptability for proper and safe use of the component or product.

RoHS

2011/65/EC

"RoHS 2011/65/EU" means that the product or part does not contain any of the substances in excess of the maximum concentration values ("MCVs") in EU RoHS Directive 2011/65/EU. The MCVs are by weight in homogeneous materials. This information represents 3M's knowledge and belief, which may be based in whole or in part on information provided by third party suppliers to 3M.

Typical Properties

Physical Properties (ASTM D1000 unless noted)	Typical Value US units (metric)
Adhesive	Thermosetting Rubber
Backing	Polyester Film
Backing Thickness ¹	1.0 Mil
Total Thickness	2.3 mils (0,058 mm)
Color	Yellow
Electrical Property (ASTM D1000 unless noted)	Typical Value US units (metric)
Temperature Class	130°C (266°F)
Dielectric Breakdown ¹	5,000 Volts
Insulation Resistance ¹ (megohms)	>1 x 10 ⁶
Breaking Strength ¹	25 lbs./in. (44 n/10 mm)
Elongation ¹ (% at break)	100
Electrolytic Corrosion Factor ²	1.0
Adhesion to Steel ¹	50 oz./in. (5,5 n/10 mm)

^{*}Footnote: 1. Test method ASTM D 1000

Not for specifications. Values are typical, not to be considered minimum or maximum. Properties measured at room temperature 73°F (23°C) unless otherwise stated



^{2. 3}M Test Method-Available on request

3MTM Polyester Film Electrical Tape 56

Specifications	3M Polyester Film Tape 56 is a polyester film-backed tape with thermosetting rubber pressure-sensitive adhesive.
	The tape shall be coated on one side with pressure-sensitive adhesive, which shall not require heat, moisture or other preparation prior to or subsequent to application. The adhesive coating shall be smooth and uniform and be free of lumps and bare spots. There shall be no separator between adjacent layers of the roll. The tape shall perform at a temperature of -40F° (-40°C) to 266°F (130°C) without substantial loss of tensile or electrical properties.
Shelf Life & Storage	This product has a 5-year shelf life from date of manufacture when stored in a humidity controlled storage (10°C/50°F to 27°C/80°F and <75% relative humidity).
Availability	3M Electrical Tape 56 is available in standard and custom widths and lengths. Standard length is 72 yards.
	Please contact your local distributor; available from 3M.com/electrical [Where to Buy] or call 1.800.676.8381.

Important Notice

All statements, technical information, and recommendations related to 3M's products are based on information believed to be reliable, but the accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use. Any statements related to the product, which are not contained in 3M's current publications, or any contrary statements contained on your purchase order, shall have no force or effect unless expressly agreed upon, in writing, by an authorized officer of 3M.

Warranty; Limited Remedy; Limited Liability

This product will be free from defects in material and manufacture at the time of purchase. 3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. Except where prohibited by law, 3M will not be liable for any indirect, special, incidental or consequential loss or damage arising from this 3M product, regardless of the legal theory asserted.

3M is a trademark of 3M Company.



Electrical Markets Division 6801 River Place Blvd. Austin, TX 78726-9000 800 676 8381 FAX: 800 828 9329 www.3M.com/oem

Please recycle © 3M 2014 All rights reserved 78-8124-4711-4 Rev B

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

3M:

<u>56 TAPE (1/4")</u> <u>56 TAPE (3/8")</u> <u>56 TAPE (1/2")</u> <u>56 Tape 1 x 72 yds</u> <u>56-YELLOW-3/4"X72YD*</u> <u>56-YELLOW-5/8"X72YD*</u>