# KPS Series, X7R Dielectric, 10 – 250 VDC (Commercial Grade) KEVET

#### **Overview**

KEMET Power Solutions (KPS) Commercial Series stacked capacitors utilize a proprietary lead-frame technology to vertically stack one or two multilayer ceramic chip capacitors into a single compact surface mount package. The attached lead-frame mechanically isolates the capacitor/s from the printed circuit board, therefore offering advanced mechanical and thermal stress performance. Isolation also addresses concerns for audible, microphonic noise that may occur when a bias voltage is applied. A two chip stack offers up to double the capacitance in the same or smaller design footprint when compared to traditional surface mount MLCCs devices. Providing up to 10 mm of board flex capability, KPS Series capacitors

are environmentally friendly and in compliance with RoHS legislation. Available in X7R dielectric, these devices are capable of Pb-Free reflow profiles and provide lower ESR, ESL and higher ripple current capability when compared to other dielectric solutions.

Combined with the stability of an X7R dielectric, KEMET's KPS Series devices exhibit a predictable change in capacitance with respect to time and voltage and boast a minimal change in capacitance with reference to ambient temperature. Capacitance change is limited to ±15% from -55°C to +125°C.

#### **Benefits**

- -55°C to +125°C operating temperature range
- · Reliable and robust termination system
- EIA 1210, 1812, and 2220 case sizes
- DC voltage ratings of 10 V, 16 V, 25 V, 50 V, 100 V, and 250 V
- Capacitance offerings ranging from 0.1  $\mu F$  up to 47  $\mu F$
- Available capacitance tolerances of ±10% and ±20%
- Higher capacitance in the same footprint
- · Potential board space savings



## **Ordering Information**

С	2220	С	106	M	5	R	2	С	7186
Ceramic	Case Size (L" x W")	Specification/ Series	Capacitance Code (pF)	Capacitance Tolerance <sup>1</sup>	Rated Voltage (VDC)	Dielectric	Failure Rate/Design	Leadframe Finish <sup>2</sup>	Packaging/ Grade (C-Spec)
	1210 1812 2220	C = Standard	Two significant digits + number of zeros	K = ±10% M = ±20%	8 = 10 4 = 16 3 = 25 5 = 50 1 = 100 A = 250	R = X7R	1 = KPS Single Chip Stack 2 = KPS Double Chip Stack	C = 100% Matte Sn	See "Packaging C-Spec Ordering Options Table" below

<sup>&</sup>lt;sup>1</sup> Double chip stacks ("2" in the 13th character position of the ordering code) are only available in M ( $\pm$ 20%) capacitance tolerance. Single chip stacks ("1" in the 13th character position of the ordering code) are available in K ( $\pm$ 10%) or M ( $\pm$ 20%) tolerances.

<sup>&</sup>lt;sup>2</sup> Additional leadframe finish options may be available. Contact KEMET for details.



## **Packaging C-Spec Ordering Options Table**

Packaging Type <sup>1</sup>	Packaging/Grade Ordering Code (C-Spec) <sup>2</sup>
7" Reel (Embossed Plastic Tape)/Unmarked	7186
13" Reel (Embossed Plastic Tape)/Unmarked	7289

<sup>&</sup>lt;sup>1</sup> The terms "Marked" and "Unmarked" pertain to laser marking option of capacitors. All packaging options labeled as "Unmarked" will contain capacitors that have not been laser marked. The option to laser mark is not available on these devices. For more information see "Capacitor Marking".

#### Benefits cont'd

- Advanced protection against thermal and mechanical stress
- · Provides up to 10 mm of board flex capability
- · Reduces audible, microphonic noise
- · Extremely low ESR and ESL

- · Lead (Pb)-free, RoHS and REACH compliant
- Capable of Pb-free reflow profiles
- · Non-polar device, minimizing installation concerns
- · Tantalum and electrolytic alternative

## **Applications**

Typical applications include smoothing circuits, DC/DC converters, power supplies (input/output filters), noise reduction (piezoelectric/mechanical), circuits with a direct battery or power source connection, critical and safety relevant circuits without (integrated) current limitation and any application that is subject to high levels of board flexure or temperature cycling. Markets include industrial, military, automotive and telecom.

#### **Qualification/Certification**


Commercial Grade products are subject to internal qualification. Details regarding test methods and conditions are referenced in Table 4, Performance & Reliability.


## **Environmental Compliance**


Lead (Pb)-free, RoHS, and REACH compliant without exemptions.



#### **Dimensions - Millimeters (Inches)**







Single Chip Stack

Number of Chips	EIA Size Code	Metric Size Code	L Length	W Width	H Height	LW Lead Width	Mounting Technique
	1210	3225	3.50 (0.138) ±0.30 (.012)	2.60 (0.102) ±0.30 (.012)	3.35 (0.132) ±0.10 (.004)	0.80 (0.032) ±0.15 (0.006)	
Single	1812	4532	5.00 (0.197) ±0.50 (.020)	3.50 (0.138) ±0.50 (.020)	2.65 (0.104) ±0.35 (0.014)	1.10 (0.043) ±0.30 (0.012)	
	2220	5650	6.00 (0.236) ±0.50 (.020)	5.00 (0.197) ±0.50 (.020)	3.50 (0.138) ±0.30 (0.012)	1.60 (0.063) ±0.30 (0.012)	Solder Reflow
	1210	3225	3.50 (0.138) ±0.30 (0.012)	2.60 (0.102) ±0.30 (.012)	6.15 (0.242) ±0.15 (0.006)	0.80 (0.031) ±0.15 (0.006)	Only
Double	1812	4532	5.00 (0.197) ±0.50 (0.020)	3.50 (0.138) ±0.50 (0.020)	5.00 (0.197) ±0.50 (0.020)	1.10 (0.043) ±0.30 (0.012)	
	2220	5650	6.00 (0.236) ±0.50 (.020)	5.00 (0.197) ±0.50 (0.020)	5.00 (0.197) ±0.50 (0.020)	1.60 (0.063) ±0.30 (0.012)	

## **Electrical Parameters/Characteristics**

Item	Parameters/Characteristics
Operating Temperature Range	-55°C to +125°C
Capacitance Change with Reference to +25°C and 0 Vdc Applied (TCC)	±15%
<sup>1</sup> Aging Rate (Maximum % Capacitance Loss/Decade Hour)	3.0%
<sup>2</sup> Dielectric Withstanding Voltage (DWV)	250% of rated voltage (5±1 seconds and charge/discharge not exceeding 50mA)
<sup>3</sup> Dissipation Factor (DF) Maximum Limit at 25°C	5%(10V), 3.5%(16V & 25V) and 2.5%(50V to 250V)
<sup>4</sup> Insulation Resistance (IR) Minimum Limit at 25°C	See Insulation Resistance Limit Table (Rated voltage applied for 120±5 seconds at 25°C)

<sup>&</sup>lt;sup>1</sup> Regarding Aging Rate: Capacitance measurements (including tolerance) are indexed to a referee time of 48 or 1,000 hours. Please refer to a part number specific datasheet for referee time details.

1 kHz  $\pm 50$  Hz and 1.0  $\pm 0.2$  Vrms if capacitance  $\leq 10~\mu F$ 

120 Hz  $\pm$ 10 Hz and 0.5  $\pm$ 0.1 Vrms if capacitance > 10  $\mu$ F

Note: When measuring capacitance it is important to ensure the set voltage level is held constant. The HP4284 and Agilent E4980 have a feature known as Automatic Level Control (ALC). The ALC feature should be switched to "ON."

<sup>&</sup>lt;sup>2</sup> DWV is the voltage a capacitor can withstand (survive) for a short period of time. It exceeds the nominal and continuous working voltage of the capacitor.

 $<sup>^{\</sup>scriptscriptstyle 3}$  Capacitance and dissipation factor (DF) measured under the following conditions:

<sup>&</sup>lt;sup>4</sup> To obtain IR limit, divide  $M\Omega$ - $\mu$ F value by the capacitance and compare to  $G\Omega$  limit. Select the lower of the two limits.



#### **Post Environmental Limits**


High Temperature Life, Biased Humidity, Moisture Resistance											
Dielectric	Rated DC Voltage	Capacitance Value	Dissipation Factor (Maximum %)	Capacitance Shift	Insulation Resistance						
	> 25		3.0								
X7R	16/25	All	5.0	±20%	10% of Initial Limit						
	< 16		7.5								

#### **Insulation Resistance Limit Table**


EIA Case Size	1,000 Megohm Microfarads or 100 GΩ	500 Megohm Microfarads or 10 GΩ
1210	< 0.39 µF	≥ 0.39 µF
1812	< 2.2 μF	≥ 2.2 µF
2220	< 10 μF	≥ 10 µF

## **Electrical Characteristics**

#### Z and ESR C1210C475M5R1C




#### Z and ESR C2220C225MAR2C






#### **Electrical Characteristics cont'd**


#### Z and ESR C2220C476M3R2C




#### Impedance – 1812, .10 μF, 50 V X7R




#### Impedance – 1210, .22 μF, 50 V X7R



#### ESR - 1812, .10 μF, 50 V X7R




#### ESR - 1210, .22 μF, 50 V X7R






#### **Electrical Characteristics cont'd**


Microphonics - 1210, 4.7 μF, 50 V, X7R




Microphonics – 2220, 22  $\mu$ F, 50 V, X7R



Microphonics – 2220, 47 μF, 25 V, X7R




Microphonics - 1210, 22 μF, 25 V, X7R




## **Competitive Comparision**

Microphonics – 1210, 4.7 μF, 50 V, X7R



Ripple Current (Arms) 2220, 22 μF, 50 V




Note: Refer to Table 4 for test method.




#### **Electrical Characteristics cont'd**


#### Board Flex vs. Termination Type



#### Board Flex vs. Termination Type



#### Board Flexure to 10 mm



#### Board Flexure to 10 mm






Table 1 - Capacitance Range/Selection Waterfall (1210 - 2220 Case Sizes)

		Case Size	e/Series			C1:	210C					C181:	2C			C	2220	С	
	Сар	Voltage	Code	8	4	3	5	1	Α	4	3	5	1	Α	4	3	5	1	Α
Capacitance	Code	Rated Volta	age (VDC)	10	16	25	50	100	250	16	25	50	100	250	16	25	50	100	250
	oouc	Capacitance	Tolerance											ess Coo		ļ	ļ.		,
						Sin	gle C	hip S	tack										
0.10 μF	104	K	М	F۷	F۷	F۷	F۷	FV	FV	GP	GP	GP	GP	GP	JP	JP	JP	JP	JP
0.22 μF	224	K	М	F۷	F۷	FV	FV	FV		GP	GP	GP	GP	GP	JP	JP	JP	JP	JP
0.47 μF	474	K	М	F۷	F۷	FV	FV	FV		GP	GP	GP	GP	GP	JP	JP	JP	JP	JP
1.0 μF	105	K	М	FV	FV	FV	FV	FV		GP	GP	GP	GP		JP	JP	JP	JP	JP
2.2 μF	225	K	М	FV	FV	FV	FV	FV		GP	GP	GP			JP	JP	JP	JP	
3.3 μF	335	K	М	FV	FV	FV	FV			GP	GP	GP			JP	JP	JP	JP	
4.7 μF	475	K	M	FV	FV	F۷	FV			GP	GP	GP			JP	JP	JP		
10 μF	106	K	М	FV	FV	FV				GP	GP				JP	JP	JP		
15 μF	156	K	M	FV											JP	JP			
22 μF	226	K	M	FV											JP	JP			
								chip S	tack										
0.10 μF	104		М	FW	FW	FW	FW	FW	FW	GR	GR	GR	GR	GR	JR	JR	JR	JR	JR
0.22 μF	224		М	FW	FW	FW	FW	FW	FW	GR	GR	GR	GR	GR	JR	JR	JR	JR	JR
0.47 μF	474		М	FW	FW	FW	FW	FW		GR	GR	GR	GR	GR	JR	JR	JR	JR	JR
1.0 μF	105		М	FW	FW	FW	FW	FW		GR	GR	GR	GR	GR	JR	JR	JR	JR	JR
2.2 μF	225		М	FW	FW	FW	FW	FW		GR	GR	GR	GR		JR	JR	JR	JR	JR
3.3 μF	335		М	FW	FW	FW	FW	FW		GR	GR	GR	GR		JR	JR	JR	JR	
4.7 μF	475		М	FW	FW	FW	FW	FW		GR	GR	GR			JR	JR	JR	JR	
10 μF	106		М	FW	FW	FW	FW			GR	GR	GR			JR	JR	JR		
22 μF	226		М	FW	FW	FW				GR	GR				JR	JR	JR		
33 μF	336		M	FW											JR	JR			
47 μF	476		M	FW											JR	JR			
	0	Rated Volta	age (VDC)	10	16	25	50	100	250	16	25	50	100	250	16	25	50	100	250
Capacitance	Cap	Voltage	Code	8	4	3	5	1	A	4	3	5	1	A	4	3	5	1	A
	Code	Case Size	e/Series			C1:	210C					C181:	2C			C	2220	С	

These products are protected under US Patent 8,331,078 other patents pending, and any foreign counterparts.

Table 2 - Chip Thickness/Tape & Reel Packaging Quantities

Thickness	Case	Thickness ±	Paper C	Quantity	Plastic Quantity			
Code	Size	Range (mm)	7" Reel	13" Reel	7" Reel	13" Reel		
FV	1210	3.35 ± 0.10	0	0	600	2,000		
FW	1210	6.15 ± 0.15	0	0	300	1,000		
GP	1812	2.65 ± 0.35	0	0	500	2,000		
GR	1812	5.00 ± 0.50	0	0	400	1,700		
JP	2220	3.50 ± 0.30	0	0	300	1,300		
JR	2220	5.00 ± 0.50	0	0	200	800		
Thickness	Thickness Case Thickness ± 7" Reel Code Size Range (mm) Paper Qu		7" Reel	13" Reel	7" Reel	13" Reel		
Code			Quantity	Plastic (	Quantity			


Package quantity based on finished chip thickness specifications.



#### Table 3 - KPS Land Pattern Design Recommendations (mm)

EIA SIZE CODE	METRIC SIZE	ı		(Nomin rotrusio	•	d
OODL	CODE	С	Y	X	V1	V2
1210	3225	1.50	1.14	1.75	5.05	3.40
1812	4532	2.20	1.35	2.87	6.70	4.50
2220	5650	2.69	2.08	4.78	7.70	6.00

Image at right based on an EIA 1210 case size.



#### **Soldering Process**

KEMET's KPS Series devices are compatible with IR reflow techniques. Preheating of these components is recommended to avoid extreme thermal stress. KEMET's recommended profile conditions for IR reflow reflect the profile conditions of the IPC/J-STD-020D standard for moisture sensitivity testing.


To prevent degradation of temperature cycling capability, care must be taken to prevent solder from flowing into the inner side of the lead frames (inner side of "J" lead in contact with the circuit board).

After soldering, the capacitors should be air cooled to room temperature before further processing. Forced air cooling is not recommended.

Hand soldering should be performed with care due to the difficulty in process control. If performed, care should be taken to avoid contact of the soldering iron to the capacitor body. The iron should be used to heat the solder pad, applying solder between the pad and the lead, until reflow occurs. Once reflow occurs, the iron should be removed immediately. (Preheating is required when hand soldering to avoid thermal shock.)

Profile Feature	SnPb Assembly	Pb-Free Assembly
Preheat/Soak		
Temperature Minimum (T <sub>Smin</sub> )	100°C	150°C
Temperature Maximum (T <sub>Smax</sub> )	150°C	200°C
Time $(t_s)$ from $T_{smin}$ to $T_{smax}$ )	60 - 120 seconds	60 - 120 seconds
Ramp-up Rate $(T_L \text{ to } T_P)$	3°C/seconds maximum	3°C/seconds maximum
Liquidous Temperature (T <sub>L</sub> )	183°C	217°C
Time Above Liquidous (t <sub>L</sub> )	60 - 150 seconds	60 - 150 seconds
Peak Temperature (T <sub>P</sub> )	235°C	250°C
Time within 5°C of Maximum Peak Temperature (t <sub>p</sub> )	20 seconds maximum	10 seconds maximum
Ramp-down Rate $(T_p \text{ to } T_L)$	6°C/seconds maximum	6°C/seconds maximum
Time 25°C to Peak Temperature	6 minutes maximum	8 minutes maximum

Note: All temperatures refer to the center of the package, measured on the package body surface that is facing up during assembly reflow.





#### Table 4 - Performance & Reliability: Test Methods and Conditions


Stress	Reference	Test or Inspection Method
Terminal Strength	JIS-C-6429	Appendix 1, Note: Force of 1.8 kg for 60 seconds.
Board Flex	JIS-C-6429	Appendix 2, Note: 5.0 mm minimum
		Magnification 50 X. Conditions:
0.11.1275		a) Method B, 4 hours at 155°C, dry heat at 235°C
Solderability	J-STD-002	b) Method B at 215°C category 3
		c) Method D, category 3 at 250°C
Temperature Cycling	JESD22 Method JA-104	1,000 cycles (-55°C to +125°C). Measurement at 24 hours +/- 4 hours after test conclusion.
Biased Humidity	MIL-STD-202 Method 103	Load Humidity: 1,000 hours 85°C/85% RH and rated voltage. Add 100 K ohm resistor.  Measurement at 24 hours +/- 4 hours after test conclusion.  Low Volt Humidity: 1,000 hours 85°C/85% RH and 1.5 V. Add 100 K ohm resistor.  Measurement at 24 hours +/- 4 hours after test conclusion.
Moisture Resistance	MIL-STD-202 Method 106	t = 24 hours/cycle. Steps 7a and 7b not required.  Measurement at 24 hours +/- 4 hours after test conclusion.
Thermal Shock	MIL-STD-202 Method 107	-55°C/+125°C. Note: Number of cycles required – 300. Maximum transfer time – 20 seconds. Dwell time – 15 minutes. Air-Air.
High Temperature Life	MIL-STD-202 Method 108	1,000 hours at 125°C with 1.5X rated voltage applied.
Storage Life	MIL-STD-202 Method 108	150°C, 0 VDC for 1,000 hours.
Vibration MIL-STD-202 Method 204		5 g's for 20 minutes, 12 cycles each of 3 orientations. Note: Use 8" X 5" PCB .031" thick, 7 secure points on one long side and 2 secure points at corners of opposite sides. Parts mounted within 2" from any secure point. Test from 10 – 2,000 Hz.
Mechanical Shock	MIL-STD-202 Method 213	Figure 1 of Method 213, Condition F.
Resistance to Solvents	MIL-STD-202 Method 215	Add aqueous wash chemical, OKEM Clean or equivalent.

## **Storage & Handling**

Ceramic chip capacitors should be stored in normal working environments. While the chips themselves are quite robust in other environments, solderability will be degraded by exposure to high temperatures, high humidity, corrosive atmospheres, and long term storage. In addition, packaging materials will be degraded by high temperature-reels may soften or warp and tape peel force may increase. KEMET recommends that maximum storage temperature not exceed 40°C and maximum storage humidity not exceed 70% relative humidity. Temperature fluctuations should be minimized to avoid condensation on the parts and atmospheres should be free of chlorine and sulfur bearing compounds. For optimized solderability chip stock should be used promptly, preferably within 1.5 years of receipt.



#### **Construction (Typical)**



## **Product Marking**

Laser marking option is not available on:

- COG, Ultra Stable X8R and Y5V dielectric devices
- EIA 0402 case size devices
- EIA 0603 case size devices with Flexible Termination option.
- · KPS Commercial and Automotive grade stacked devices.

These capacitors are supplied unmarked only.



#### **Tape & Reel Packaging Information**

KEMET offers multilayer ceramic chip capacitors packaged in 8, 12 and 16 mm tape on 7" and 13" reels in accordance with EIA Standard 481. This packaging system is compatible with all tape-fed automatic pick and place systems. See Table 2 for details on reeling quantities for commercial chips.




Table 5 - Carrier Tape Configuration - Embossed Plastic (mm)


EIA Case Size	Tape Size (W)*	Pitch (P <sub>1</sub> )*
01005 - 0402	8	2
0603 - 1210	8	4
1805 - 1808	12	4
≥ 1812	12	8
KPS 1210	12	8
KPS 1812 & 2220	16	12
Array 0508 & 0612	8	4

<sup>\*</sup>Refer to Figure 1 for W and  $P_1$  carrier tape reference locations.

<sup>\*</sup>Refer to Table 5 for tolerance specifications.



#### Figure 1 - Embossed (Plastic) Carrier Tape Dimensions



## **Table 6 - Embossed (Plastic) Carrier Tape Dimensions**

Metric will govern

Constant Dimensions — Millimeters (Inches)									
Tape Size	D <sub>0</sub>	D <sub>1</sub> Minimum Note 1	E <sub>1</sub>	P <sub>0</sub>	P <sub>2</sub>	R Reference Note 2	S <sub>1</sub> Minimum Note 3	T Maximum	T <sub>1</sub> Maximim
8 mm		1.0 (0.039)				25.0 (0.984)			
12 mm	1.5+0.10/0.0-0.0 (0.059+0.004/-0.0)	1.5	1.75±0.10 (0.069±0.004)	4.0±0.10 (0.157±0.004)	2.0±0.05 (0.079±0.002)	30	0.600 (0.024)	0.600 (0.024)	0.100 (0.004)
16 mm		(0.059)				(1.181)			
Variable Dimensions — Millimeters (Inches)									
Tape Size	Pitch	B <sub>1</sub> Maximum Note 4	E <sub>2</sub> Minimum	F	P <sub>1</sub>	T <sub>2</sub> Maximum	W Maximum	A <sub>0</sub> , B <sub>0</sub>	, & K <sub>0</sub>
8 mm	Single (4 mm)	4.35 (0.171)	6.25 (0.246)	3.5±0.05 (0.138±0.002)	4.0±0.10 (0.157±0.004)	2.5 (0.098)	8.3 (0.327)		
12 mm	Single (4 mm) & Double (8 mm)	8.2 (0.323)	10.25 (0.404)	5.5±0.05 (0.217±0.002)	8.0±0.10 (0.315±0.004)	4.6 (0.181)	12.3 (0.484)	Note 5	
16 mm	Triple (12 mm)	12.1 (0.476)	14.25 (0.561)	7.5±0.05 (0.138±0.002)	12.0±0.10 (0.157±0.004)	4.6 (0.181)	16.3 (0.642)		

- 1. The embossment hole location shall be measured from the sprocket hole controlling the location of the embossment. Dimensions of embossment location and hole location shall be applied independent of each other.
- 2. The tape with or without components shall pass around R without damage (see Figure 5).
- 3. If  $S_1 < 1.0$  mm, there may not be enough area for cover tape to be properly applied (see EIA Standard 481 paragraph 4.3 section b).
- 4.  $B_1$  dimension is a reference dimension for tape feeder clearance only.
- 5. The cavity defined by  $A_{o}$ ,  $B_{o}$  and  $K_{o}$  shall surround the component with sufficient clearance that:
  - (a) the component does not protrude above the top surface of the carrier tape.
  - (b) the component can be removed from the cavity in a vertical direction without mechanical restriction, after the top cover tape has been removed.
  - (c) rotation of the component is limited to 20° maximum for 8 and 12 mm tapes and 10° maximum for 16 mm tapes (see Figure 2).
  - (d) lateral movement of the component is restricted to 0.5 mm maximum for 8 and 12 mm wide tape and to 1.0 mm maximum for 16 mm tape (see Figure 3).
  - (e) for KPS Series product,  $A_n$  and  $B_n$  are measured on a plane 0.3 mm above the bottom of the pocket.
  - (f) see Addendum in EIA Standard 481 for standards relating to more precise taping requirements.



## **Packaging Information Performance Notes**

1. Cover Tape Break Force: 1.0 Kg minimum.


2. Cover Tape Peel Strength: The total peel strength of the cover tape from the carrier tape shall be:


Tape Width	Peel Strength		
8 mm	0.1 to 1.0 Newton (10 to 100 gf)		
12 and 16 mm	0.1 to 1.3 Newton (10 to 130 gf)		

The direction of the pull shall be opposite the direction of the carrier tape travel. The pull angle of the carrier tape shall be 165° to 180° from the plane of the carrier tape. During peeling, the carrier and/or cover tape shall be pulled at a velocity of 300 ±10 mm/minute.


3. Labeling: Bar code labeling (standard or custom) shall be on the side of the reel opposite the sprocket holes. Refer to EIA Standards 556 and 624.

#### Figure 2 - Maximum Component Rotation





## Figure 3 - Maximum Lateral Movement



## Figure 4 - Bending Radius







Figure 5 - Reel Dimensions



Note: Drive spokes optional; if used, dimensions B and D shall apply.


**Table 7 - Reel Dimensions** 

Metric will govern


Constant Dimensions — Millimeters (Inches)							
Tape Size	A	B Minimum	С	D Minimum			
8 mm	178 ±0.20		13.0 +0.5/-0.2 (0.521 +0.02/-0.008)	20.2 (0.795)			
12 mm	(7.008 ±0.008) or	1.5 (0.059)					
16 mm	330 ±0.20 (13.000 ±0.008)	(* ** )	(* * * * * * * * * * * * * * * * * * *				
	Variable Dimensions — Millimeters (Inches)						
Tape Size	N Minimum	$W_1$	W <sub>2</sub> Maximum	W <sub>3</sub>			
8 mm		8.4 +1.5/-0.0 (0.331 +0.059/-0.0)	14.4 (0.567)				
12 mm	50 (1.969)	12.4 +2.0/-0.0 (0.488 +0.078/-0.0)	18.4 (0.724)	Shall accommodate tape width without interference			
16 mm		16.4 +2.0/-0.0 (0.646 +0.078/-0.0)	22.4 (0.882)				



#### Figure 6 - Tape Leader & Trailer Dimensions



## Figure 7 - Maximum Camber





#### **KEMET Electronic Corporation Sales Offices**

For a complete list of our global sales offices, please visit www.kemet.com/sales.

#### **Disclaimer**

All product specifications, statements, information and data (collectively, the "Information") in this datasheet are subject to change. The customer is responsible for checking and verifying the extent to which the Information contained in this publication is applicable to an order at the time the order is placed.

All Information given herein is believed to be accurate and reliable, but it is presented without guarantee, warranty, or responsibility of any kind, expressed or implied.

Statements of suitability for certain applications are based on KEMET Electronics Corporation's ("KEMET") knowledge of typical operating conditions for such applications, but are not intended to constitute – and KEMET specifically disclaims – any warranty concerning suitability for a specific customer application or use. The Information is intended for use only by customers who have the requisite experience and capability to determine the correct products for their application. Any technical advice inferred from this Information or otherwise provided by KEMET with reference to the use of KEMET's products is given gratis, and KEMET assumes no obligation or liability for the advice given or results obtained.

Although KEMET designs and manufactures its products to the most stringent quality and safety standards, given the current state of the art, isolated component failures may still occur. Accordingly, customer applications which require a high degree of reliability or safety should employ suitable designs or other safeguards (such as installation of protective circuitry or redundancies) in order to ensure that the failure of an electrical component does not result in a risk of personal injury or property damage.

Although all product-related warnings, cautions and notes must be observed, the customer should not assume that all safety measures are indicted or that other measures may not be required.

# **Mouser Electronics**

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

# Kemet:

C2220C225MAR2CTU	C1210C225K1R1CT500	C2220C335K5R1CT500	C1210C105K1R1CT500
C2220C105MAR2CT500	C1812C226M4R2CT500	C1812C106M3R2CT500	C1812C335M5R2CT500
C1812C474MAR2CT500	C2220C476M3R2CT500	C2220C336M4R2CT500	C2220C106K3R1CT500
C2220C106K5R1CT500	C2220C106M5R2CT500	C2220C225MAR2CT500	C2220C225M1R2CT500
C2220C335K1R1CT500	C1210C475M1R2CT500	C2220C226M5R2CT500	C1210C475K5R1CT500
C1812C105MAR2CT500	C2220C105MAR1C7186	C2220C226K3R1CTU (	C2220C475M1R2C7186
C2220C225MAR2C7186	C1210C225K1R1CTU C	C1210C226M3R2CTU C2	220C476M3R2CTU