

STATSHIELD® METAL-IN SERIES



Specifications:

Standard Document

ANSI/ESD S541 (ANSI/ESD S20.20)
ANSI/ESD S11.4

Electrical Properties

Surface Resistance:

Outer Surface
Inner Surface
Discharge Shielding
Charge Generation

Capacitance Probe (to dissipate 1 kV)

Typical Values

1×10^4 to $< 1 \times 10^{11}$ ohms
 1×10^4 to $< 1 \times 10^{11}$ ohms
<20 nJ
Teflon: 0.09 nC/sq. in.
Quartz: 0.01 nC/sq. in.
<30 volts

Physical Properties

Film Thickness
Width (Inside Dimensions)
Length (Inside Dimensions)
Light Transmission
Heat Seal
Tensile Strength
Puncture Resistance
Non-corrosive
Silicone
Marking Adhesion

Nominal 0.0030" (0.0762mm) $\pm 10\%$
Nominal -0" / + 0.125"
Nominal ± 0.125 "
>40% (Tobias)
>10 lbs/in
4600 PSI, 32 MPa
>10 lbs
Pass
Not detected
Pass

Meets Requirements of:

ESD Protective Packaging
Level 3 Technical Requirements

Test Procedures/Method

ANSI/ESD STM11.11
ANSI/ESD STM11.11
ANSI/ESD STM11.31, EIA 541
Modified Incline Plane
Modified Incline Plane
ANSI/EIA-541/Appendix E, 1kV Discharge


MIL-STD-3010, 1003

ASTM D-1003
375°F, 1/2 sec 60 psi
ASTM D882
MIL-STD-3010, 2065
MIL-STD-3010, M3005
FTIR
IPC-TM-650 2.4.1

Low Charging Static
Dissipative Proprietary
Outer Polyester Layer

Aluminum Shielding Layer

Low Charging Static
Dissipative Proprietary
Inner Polyethylene Layer



ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

1. Low charge generation
2. Dissipative or conductive materials for intimate contact
3. A structure that provides electrostatic discharge shielding."

RoHS 2, REACH and Conflict Minerals Statement

None of the RoHS 2 restricted materials, REACH substances of very high concern as of 2016/06/20, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Desco Industries Inc. [Limited Warranty at Desco.com](#).



Mixed Unsortable Plastic Scrap

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Desco's bags are recyclable

Statshield® bags are packaged 100 per package in an oversized shielding bag.
See Shielding Bag Storage at [TB-7057](#).

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc.
See Bag Selection Chart Click [HERE](#).



Made in the
United States of America

Specifications and procedures subject to change without notice.

STATSHIELD® BAG, SHIELDING, METAL-IN, 0.0030" (0.0762mm)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: [Desco.com](#)
PHONE (909) 627-8178

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407
PHONE (781) 821-8370

**DRAWING
NUMBER**
13405

DATE:
August
2016

DESCO

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Desco:

[13430](#) [13445](#) [13465](#) [13470](#) [13415](#) [13460](#) [13405](#) [13505](#) [13524](#)