

ESD Cellulose Tape

For general purpose applications

- 2.4 mil (0.06 mm) total thickness
- Cellulose firm resistance 1×10^{10} to $< 1 \times 10^{12}$ ohms per IEC 61340-2-3
- Rubber based adhesive absorbs moisture
- Adhesive surface resistance 1 x 10¹⁰ to < 1 x 10¹² ohms per IEC 61340-2-3
- Temperature Range -10°C to +71°C (14°F 160°F); meets MIL-B-81705 of 100°C for 10 min max
- Available only in clear

Replace regular adhesive tapes with ESD tapes complying with EN 61340-5

- "All generators of electrostatic charges, such as untreated plastic films, foams, synthetic fibres, adhesive tapes, etc., must be prohibited and should be kept away from the EPA [ESD protected areal." (EN 61340-5-2 section 6)
- "EPA should never have any electrostatic generative adhesive tapes or labels, as these can cause very high potentials when applied or stripped off." (EN 61340-5-1 section 7.4)

Таре	12 mm	18 mm	24 mm	48 mm	Core	Length
ESD Clear Cellulose	<u>242290</u>	<u>242291</u>	<u>242292</u>		25.4 mm	32.9 m
ESD Clear Cellulose	<u>242293</u>	<u>242294</u>	<u>242295</u>	<u>242296</u>	76.2 mm	65.8 m

Width tolerance ±0.8 mm

Tape widths are nominal metric ±0.8 mm									
	6				0.236" ±.031				
					0.472" ±.031				
					0.709" ±.031				
	-				0.945" ±.031				
					1.890" ±.031				
く						/			

ESD CELLULUSE TAPE, PLASTIC CORE

VERMASON UNIT C, 4TH DIMENSION, FOURTH AVENUE, LETCHWORTH, HERTS, SG6 2TD UK PHONE: +44 (0) 1462-672005 FAX: +44 (0) 1462-670440 E-MAIL: Service@Vermason.co.uk INTERNET: Vermason.co.uk



RoHS 2. REACH. and Conflict Minerals Statement

None of the RoHS 2 restricted materials, or REACH substances of very high concern as of 2015/12/17, or Conflict Minerals are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Vermason Terms and Conditions

No chlorine, latex, sulfur, surfactants or silicone based material (adhesive, film backing, release material) is used in the manufacture of our cellulose tape.

Wescorp Tape Storage and Limited Warranty:

The user must determine the suitability for use of an ESD tape for his particular application. For best results, tape inventory should be continually replenished. It is recommended that rolls of tape be stored flat and rotated (flipped over to the other side) periodically. Tapes should be stored in a dry, well ventilated room with a reasonably consistent temperature of 68°F (20°C) and be protected from exposure to direct sunlight. Tape should not be stored in ultraviolet sunlight, moisture, or heat. Tape over one year old should be evaluated by the user to determine acceptability for the user's application. Vermason recommends those tracking useful life of product to use shipping/invoice date as Vermason expressly warrants that for a period of one (1) vear from the date of purchase, our Wescorp Brand ESD Tape will be free of defects in material (parts) and workmanship (labour). See details of Limited Warranty online at Vermason.co.uk

