SPECIFICATION CONTROL DRAWING

WIRE, SOLID, TIN-COATED COPPER AND ELECTROLYTIC TIN-COATED OXYGEN-FREE COPPER, GENERAL PURPOSE, 600 VOLT Date 08-09-03 44/7004

M

This specification sheet forms a part of the latest issue of Raychem Specification 44.

CONDUCTOR -SOLIDTIN-COATED COPPER (AWG 22 - 16)

ELECTROLYTICTIN-COATED

OXYGEN-FREE COPPER (AWG 26 - 24)

PRIMARY INSULATON-RADIATION-CROSSLINKED, EXTRUDED POLYALKENE JACKET - RADIATION-CROSSLINKED

MODIFIEDPVF₂

Thickness: $.003 \pm .001$ in.

TABLE I. CONSTRUCTION DETAILS									
	WIRE SIZE (AWG)	MAXIMUM DIAMETER CONDUCTOR (in.)	FINISHED WIRE						
PART NUMBER 1/			MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft.)	DIAMETER (in.)	MAXIMUM WEIGHT (lb/1000 ft.)				
44/7004-26-*	26	.017	46.2	.030 ± .002	1.2				
44/7004-24-*	24	.021	28.3	.035 ± .002	1.7				
44/7004-22-*	22	.026	17.9	.040 ± .002	2.6				
44/7004-20-*	20	.033	11.2	.047 ± .002	3.9				
44/7004-18-*	18	.042	7.0	.055 ± .002	5.9				
44/7004-16-*	16	.052	4.4	.066 ± .002	9.2				

	TABLE II. PE	RFORMANCE	DETAILS					
PART NUMBER 1/	BENDTESTING							
	MANDREL DIA (in.) (± 3	WEIGHT (lb) (± 3%)						
	LIFE CYCLE AND ACCELERATED AGING	COLD BEND	WRAP	LIFE CYCLE AND ACCELERATED AGING	COLD BEND			
44/7004-26-*	.500	.500	.250	.125	.500			
44/7004-24-*	.500	.500	.250	.190	.500			
44/7004-22-*	.750	.750	.375	.190	1.00			
44/7004-20-*	.750	.750	.375	.190	1.00			
44/7004-18-*	1.00	1.00	.500	.250	1.00			
44/7004-16-*	1.00	1.00	.500	.250	1.00			

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 135°C

Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level ACCELERATED AGING: 225 ± 2°C for 6 hours

BLOCKING: 150 ± 2°C for 24 hours

COLOR: White preferred

CONCENTRICITY: (Entire insulation only) 70% (minimum) FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum);

no flaming of facial tissue

HUMIDITY RESISTANCE: Insulation Resistance,

5000 megohms for 1000 ft. (minimum)

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Elongation, 150% (minimum)

Tensile Strength, 3000 lbf/in2 (minimum) INSULATION RESISTANCE: 5000 megohms for

1000 ft. (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 4.2 kV (rms) at 3.0 kHz Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire,

Spark Test, 5.7 kV (rms) at 3.0 kHz Impulse Dielectric Test, 8.0 kV (peak) LIFE CYCLE: 185 ± 3°C for 120 hours

LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours

SMOKE: 165 ± 2°C. No visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum),

both readings

VOLTAGE WITHSTAND TEST (Post Environmental):

2500 volts (rms), 60 Hz, 5 minutes WICKING: 2.25 in. (maximum)

PART NUMBER:

The "*" in the part numbers above shall be replaced with a color code designator.

1/ Example: AWG 26, white; 44/7004-26-9

AWG 26, white with black stripe; 44/7004-26-90

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL

Page 1 of 1

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID



Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TE Connectivity: 44/7004-22-9CS1059