

SPECIFICATION

SPEC. No. C-General-c

D A T E : 2016 Jan.

To

Non-Controlled Copy

CUSTOMER'S PRODUCT NAME

TDK PRODUCT NAME

MULTILAYER CERAMIC CHIP CAPACITORS

C Series / Commercial Grade

General (Up to 50V)

Mid voltage (100 to 630V)

Please return this specification to TDK representatives.

If orders are placed without returned specification, please allow us to judge that specification is accepted by your side.

RECEIPT CONFIRMATION

DATE: YEAR MONTH DAY

TDK Corporation

Sales

Electronic Components

Sales & Marketing Group

Engineering

Electronic Components Business Company

Ceramic Capacitors Business Group

APPROVED	Person in charge

APPROVED	CHECKED	Person in charge

1. SCOPE

This specification is applicable to chip type multilayer ceramic capacitors with a priority over the other relevant specifications.

Production places defined in this specification shall be TDK Corporation Japan,
TDK (Suzhou) Co., Ltd and TDK Components U.S.A. Inc.

EXPLANATORY NOTE:

This specification warrants the quality of the ceramic chip capacitors. The chips should be evaluated or confirmed a state of mounted on your product.


If the use of the chips goes beyond the bounds of the specification, we can not afford to guarantee.

2. CODE CONSTRUCTION

(Example)

Catalog Number :	<u>C2012</u>	<u>X7R</u>	<u>1E</u>	<u>105</u>	<u>K</u>	<u>125</u>	<u>A</u>	<u>A</u>
(Web)	(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
Item Description :	<u>C2012</u>	<u>X7R</u>	<u>1E</u>	<u>105</u>	<u>K</u>	<u>T</u>	<u>xxxx</u>	
	(1)	(2)	(3)	(4)	(5)	(9)	(10)	

(1) Type



Please refer to product list for the dimension of each product.

(2) Temperature Characteristics (Details are shown in table 1 No.7 and No.8 at page 5)

(3) Rated Voltage

Symbol	Rated Voltage
2 J	DC 630 V
2 W	DC 450 V
2 V	DC 350 V
2 E	DC 250 V
2 A	DC 100 V
1 H	DC 50 V
1 V	DC 35 V
1 E	DC 25 V
1 C	DC 16 V
1 A	DC 10 V
0 J	DC 6.3 V
0 G	DC 4 V

(4) Rated Capacitance

Stated in three digits and in units of pico farads (pF).

The first and Second digits identify the first and second significant figures of the capacitance, the third digit identifies the multiplier.

R is designated for a decimal point.

Example 2R2 → 2.2pF

105 → 1,000,000pF

(5) Capacitance tolerance

Symbol	Tolerance	Capacitance
B	± 0.1 pF	10pF and under
C	± 0.25 pF	
D	± 0.5 pF	
J	± 5 %	Over 10pF
K	± 10 %	
M	± 20 %	

(6) Thickness code (Only Catalog Number)

(7) Package code (Only Catalog Number)

(8) Special code (Only Catalog Number)

(9) Packaging (Only Item Description)

Symbol	Packaging
B	Bulk
T	Taping

(10) Internal code (Only Item Description)

3. RATED CAPACITANCE AND CAPACITANCE TOLERANCE

3.1 Standard combination of rated capacitance and tolerances

Class	Temperature Characteristics	Capacitance tolerance		Rated capacitance
1	C H C0G	10pF and under	B (± 0.1 pF) C (± 0.25 pF)	0.5, 1, 1.5, 2, 2.2, 3, 3.3, 4, 4.7, 5
			D (± 0.5 pF)	6, 6.8, 7, 8, 9, 10
		12pF to 10,000pF	J (± 5 %) K (± 10 %)	E – 12 series
		Over 10,000pF		E – 6 series
2	J B X5R X6S X7R X7S X7T	10uF and under	K (± 10 %) M (± 20 %)	E – 6 series
		Over 10uF	M (± 20 %)	

3.2 Capacitance Step in E series

E series	Capacitance Step											
E-3	1.0				2.2				4.7			
E-6	1.0		1.5		2.2		3.3		4.7		6.8	
E-12	1.0	1.2	1.5	1.8	2.2	2.7	3.3	3.9	4.7	5.6	6.8	8.2

4. OPERATING TEMPERATURE RANGE

T.C.	Min. operating Temperature	Max. operating Temperature	Reference Temperature
C H J B	-25°C	85°C	20°C
X5R	-55°C	85°C	25°C
X6S	-55°C	105°C	25°C
X7R X7S X7T C0G	-55°C	125°C	25°C

5. STORING CONDITION AND TERM

5 to 40°C at 20 to 70%RH

6 months Max.

6. P.C. BOARD

When mounting on an aluminum substrate, large case sizes such as C3225, C4532 and C5750 types are more likely to be affected by heat stress from the substrate.

Please inquire separate specification for the large case sizes when mounted on the substrate.

7. INDUSTRIAL WASTE DISPOSAL



Dispose this product as industrial waste in accordance with the Industrial Waste Law.

8. PERFORMANCE


table 1

No.	Item	Performance	Test or inspection method																				
1	External Appearance	No defects which may affect performance.	Inspect with magnifying glass (3×), in case of C0402 and C0603 type, with magnifying glass (10×)																				
2	Insulation Resistance	10,000MΩ or 500MΩ·μF min. (As for the capacitors of rated voltage 16, 10V DC and lower, 10,000 MΩ or 100MΩ·μF min.,) whichever smaller.	Apply rated voltage for 60s.																				
3	Voltage Proof	Withstand test voltage without insulation breakdown or other damage.	<table><tr><th>Class</th><th>Rated voltage</th><th>Apply voltage</th></tr><tr><td rowspan="3">Class1</td><td>100V and under</td><td>3 × rated voltage</td></tr><tr><td>Over 100V 500V and under</td><td>1.5 × rated voltage</td></tr><tr><td>Over 500V</td><td>1.3 × rated voltage</td></tr><tr><td rowspan="3">Class2</td><td>100V and under</td><td>2.5 × rated voltage</td></tr><tr><td>Over 100V 500V and under</td><td>1.5 × rated voltage</td></tr><tr><td>Over 500V</td><td>1.3 × rated voltage</td></tr></table> <p>Above DC voltage shall be applied for 1s. Charge / discharge current shall not exceed 50mA.</p>	Class	Rated voltage	Apply voltage	Class1	100V and under	3 × rated voltage	Over 100V 500V and under	1.5 × rated voltage	Over 500V	1.3 × rated voltage	Class2	100V and under	2.5 × rated voltage	Over 100V 500V and under	1.5 × rated voltage	Over 500V	1.3 × rated voltage			
Class	Rated voltage	Apply voltage																					
Class1	100V and under	3 × rated voltage																					
	Over 100V 500V and under	1.5 × rated voltage																					
	Over 500V	1.3 × rated voltage																					
Class2	100V and under	2.5 × rated voltage																					
	Over 100V 500V and under	1.5 × rated voltage																					
	Over 500V	1.3 × rated voltage																					
4	Capacitance	Within the specified tolerance.	<table><tr><th>Class</th><th>Rated Capacitance</th><th>Measuring frequency</th><th>Measuring voltage</th></tr><tr><td rowspan="2">Class1</td><td>1000pF and under</td><td>1MHz±10%</td><td rowspan="2">0.5-5Vrms.</td></tr><tr><td>Over 1000pF</td><td>1kHz±10%</td></tr><tr><td rowspan="3">Class2</td><td>10uF and under</td><td>1kHz±10%</td><td>0.5±0.2Vrms.</td></tr><tr><td></td><td></td><td>1.0±0.2Vrms.</td></tr><tr><td>Over 10uF</td><td>120Hz±20%</td><td>0.5±0.2Vrms.</td></tr></table> <p>For information which product has which measuring voltage, please contact with our sales representative.</p>	Class	Rated Capacitance	Measuring frequency	Measuring voltage	Class1	1000pF and under	1MHz±10%	0.5-5Vrms.	Over 1000pF	1kHz±10%	Class2	10uF and under	1kHz±10%	0.5±0.2Vrms.			1.0±0.2Vrms.	Over 10uF	120Hz±20%	0.5±0.2Vrms.
Class	Rated Capacitance	Measuring frequency	Measuring voltage																				
Class1	1000pF and under	1MHz±10%	0.5-5Vrms.																				
	Over 1000pF	1kHz±10%																					
Class2	10uF and under	1kHz±10%	0.5±0.2Vrms.																				
			1.0±0.2Vrms.																				
	Over 10uF	120Hz±20%	0.5±0.2Vrms.																				
5	Q (Class1)	<table><tr><th>Rated Capacitance</th><th>Q</th></tr><tr><td>30pF and over</td><td>1,000 min.</td></tr><tr><td>Under 30pF</td><td>400+20×C min.</td></tr></table> <p>C : Rated capacitance (pF)</p>	Rated Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20×C min.	See No.4 in this table for measuring condition.														
Rated Capacitance	Q																						
30pF and over	1,000 min.																						
Under 30pF	400+20×C min.																						
6	Dissipation Factor (Class2)	<table><tr><th>T.C.</th><th>D.F.</th></tr><tr><td>J B</td><td>0.025 max.</td></tr><tr><td>X5R</td><td>0.03 max.</td></tr><tr><td>X6S</td><td>0.05 max.</td></tr><tr><td>X7R</td><td>0.075 max.</td></tr><tr><td>X7S</td><td>0.10 max.</td></tr><tr><td>X7T</td><td>0.15 max.</td></tr></table>	T.C.	D.F.	J B	0.025 max.	X5R	0.03 max.	X6S	0.05 max.	X7R	0.075 max.	X7S	0.10 max.	X7T	0.15 max.	<p>See No.4 in this table for measuring condition.</p> <p>For information which product has which Dissipation Factor, please see the detail page of each product on the website.</p>						
T.C.	D.F.																						
J B	0.025 max.																						
X5R	0.03 max.																						
X6S	0.05 max.																						
X7R	0.075 max.																						
X7S	0.10 max.																						
X7T	0.15 max.																						

(continued)

No.	Item	Performance	Test or inspection method																												
7	Temperature Characteristics of Capacitance (Class1)	<table><tr><td>T.C.</td><td>Temperature Coefficient (ppm/°C)</td></tr><tr><td>C H</td><td>0 ± 60</td></tr><tr><td>C0G</td><td>0 ± 30</td></tr></table> <p>Capacitance drift Within ± 0.2% or ±0.05pF, whichever larger.</p>	T.C.	Temperature Coefficient (ppm/°C)	C H	0 ± 60	C0G	0 ± 30	<p>Temperature coefficient shall be calculated based on values at 25°C (CH : 20°C) and 85°C temperature.</p> <p>Measuring temperature below 20°C shall be -10°C and -25°C.</p>																						
T.C.	Temperature Coefficient (ppm/°C)																														
C H	0 ± 60																														
C0G	0 ± 30																														
8	Temperature Characteristics of Capacitance (Class2)	<table><tr><th colspan="2">Capacitance Change (%)</th></tr><tr><th>No voltage applied</th><th>With voltage applied</th></tr><tr><td>J B : ±10</td><td>J B : + 10 - 30 : + 10 - 50 : + 10 - 60 : —</td></tr><tr><td>X5R : ±15</td><td></td></tr><tr><td>X6S : ±22</td><td></td></tr><tr><td>X7R : ±15</td><td>—</td></tr><tr><td>X7S : ±22</td><td></td></tr><tr><td>X7T : +22</td><td></td></tr><tr><td>-33</td><td></td></tr></table>	Capacitance Change (%)		No voltage applied	With voltage applied	J B : ±10	J B : + 10 - 30 : + 10 - 50 : + 10 - 60 : —	X5R : ±15		X6S : ±22		X7R : ±15	—	X7S : ±22		X7T : +22		-33		<p>Capacitance shall be measured by the steps shown in the following table after thermal equilibrium is obtained for each step.</p> <p>ΔC be calculated ref. STEP3 reading</p> <table><tr><th>Step</th><th>Temperature(°C)</th></tr><tr><td>1</td><td>Reference temp. ± 2</td></tr><tr><td>2</td><td>Min. operating temp. ± 2</td></tr><tr><td>3</td><td>Reference temp. ± 2</td></tr><tr><td>4</td><td>Max. operating temp. ± 2</td></tr></table> <p>Measuring voltage: 0.1, 0.2, 0.5, 1.0Vrms. For information which product has which applied voltage, please contact with our sales representative.</p>	Step	Temperature(°C)	1	Reference temp. ± 2	2	Min. operating temp. ± 2	3	Reference temp. ± 2	4	Max. operating temp. ± 2
Capacitance Change (%)																															
No voltage applied	With voltage applied																														
J B : ±10	J B : + 10 - 30 : + 10 - 50 : + 10 - 60 : —																														
X5R : ±15																															
X6S : ±22																															
X7R : ±15	—																														
X7S : ±22																															
X7T : +22																															
-33																															
Step	Temperature(°C)																														
1	Reference temp. ± 2																														
2	Min. operating temp. ± 2																														
3	Reference temp. ± 2																														
4	Max. operating temp. ± 2																														
9	Robustness of Terminations	No sign of termination coming off, breakage of ceramic, or other abnormal signs.	<p>Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b and apply a pushing force of 2N (C0603, C1005) or 5N (C1608, C2012, C3216, C3225, C4532, C5750) with 10±1s. (Not applicable to C0402.)</p> 																												
10	Bending	No mechanical damage.	<p>Reflow solder the capacitors on a P.C.Board shown in Appendix 2a or Appendix 2b and bend it for 1mm.</p>  <p>(Unit : mm)</p>																												

(continued)

No.	Item	Performance	Test or inspection method
11	Solderability	<p>(C0402)</p> <p>Both end faces and the contact areas shall be covered with a smooth and bright solder coating with no more than a small amount of scattered imperfections such as pinholes or un-wetted or de-wetted areas. These imperfections shall not be concentrated in one area.</p> <p>(Others)</p> <p>New solder to cover over 75% of termination. 25% may have pin holes or rough spots but not concentrated in one spot. Ceramic surface of A sections shall not be exposed due to melting or shifting of termination material.</p>  <p>A section</p>	<p>Completely soak both terminations in solder at the following conditions.</p> <p>Solder : Sn-3.0Ag-0.5Cu or Sn-37Pb Temperature: 245±5°C (Sn-3.0Ag-0.5Cu) 235±5°C (Sn-37Pb) Soaking time: 3±0.3s (Sn-3.0Ag-0.5Cu) 2±0.2s (Sn-37Pb)</p> <p>Flux: Isopropyl alcohol (JIS K 8839) Rosin (JIS K 5902) 25% solid solution.</p> <p>Only reflow soldering applicable to C0402.</p> <p>Peak condition Temp. : 235±5°C Time : 2±0.5s.</p> <p>Preheating condition Temp. : 110 to 140°C Time : 30 to 60s.</p>

(continued)

No.	Item		Performance		Test or inspection method																			
12	Resistance to solder heat	External appearance	No cracks are allowed and terminations shall be covered at least 60% with new solder.		Completely soak both terminations in solder at the following conditions. 260±5°C for 10±1s. Preheating condition Temp. : 110 to 140°C Time : 30 to 60s. Solder : Sn-3.0Ag-0.5Cu or Sn-37Pb Flux : Isopropyl alcohol (JIS K 8839) Rosin (JIS K 5902) 25% solid solution. Leave the capacitors in ambient condition for 6 to 24h (Class1) or 24±2h (Class2) before measurement. Only reflow soldering applicable to C0402. Peak condition Temp. : 260°C Time : 5±0.5s. Preheating condition Temp. : 110 to 140°C Time : 30 to 60s.																			
		Capacitance	<table><tr><th colspan="2">Characteristics</th><th>Change from the value before test</th></tr><tr><td>Class 1</td><td>C H C0G</td><td>Capacitance drift within ±2.5% or ±0.25pF, whichever larger.</td></tr><tr><td rowspan="5">Class 2</td><td>J B</td><td>± 7.5 %</td></tr><tr><td>X5R</td><td>± 7.5 %</td></tr><tr><td>X6S</td><td>± 7.5 %</td></tr><tr><td>X7R</td><td>± 7.5 %</td></tr><tr><td>X7S</td><td>± 7.5 %</td></tr><tr><td>X7T</td><td>± 7.5 %</td></tr></table>			Characteristics		Change from the value before test	Class 1	C H C0G	Capacitance drift within ±2.5% or ±0.25pF, whichever larger.	Class 2	J B	± 7.5 %	X5R	± 7.5 %	X6S	± 7.5 %	X7R	± 7.5 %	X7S	± 7.5 %	X7T	± 7.5 %
		Characteristics		Change from the value before test																				
		Class 1	C H C0G	Capacitance drift within ±2.5% or ±0.25pF, whichever larger.																				
		Class 2	J B	± 7.5 %																				
			X5R	± 7.5 %																				
			X6S	± 7.5 %																				
X7R	± 7.5 %																							
X7S	± 7.5 %																							
X7T	± 7.5 %																							
Q (Class1)	<table><tr><th>Rated Capacitance</th><th>Q</th></tr><tr><td>30pF and over</td><td>1,000 min.</td></tr><tr><td>Under 30pF</td><td>400+20xC min.</td></tr></table> C : Rated capacitance (pF)		Rated Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20xC min.																
Rated Capacitance	Q																							
30pF and over	1,000 min.																							
Under 30pF	400+20xC min.																							
D.F. (Class2)	Meet the initial spec.																							
Insulation Resistance	Meet the initial spec.																							
Voltage proof	No insulation breakdown or other damage.																							
13	Vibration	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b before testing. Vibrate the capacitors with amplitude of 1.5mm P-P changing the frequencies from 10Hz to 55Hz and back to 10Hz in about 1min. Repeat this for 2h each in 3 perpendicular directions.																			
		Capacitance	<table><tr><th colspan="2">Characteristics</th><th>Change from the value before test</th></tr><tr><td>Class1</td><td>C H C0G</td><td>±2.5% or ±0.25pF, whichever larger.</td></tr><tr><td rowspan="5">Class2</td><td>J B</td><td>± 7.5 %</td></tr><tr><td>X5R</td><td>± 7.5 %</td></tr><tr><td>X6S</td><td>± 7.5 %</td></tr><tr><td>X7R</td><td>± 7.5 %</td></tr><tr><td>X7S</td><td>± 7.5 %</td></tr><tr><td>X7T</td><td>± 7.5 %</td></tr></table>			Characteristics		Change from the value before test	Class1	C H C0G	±2.5% or ±0.25pF, whichever larger.	Class2	J B	± 7.5 %	X5R	± 7.5 %	X6S	± 7.5 %	X7R	± 7.5 %	X7S	± 7.5 %	X7T	± 7.5 %
		Characteristics		Change from the value before test																				
		Class1	C H C0G	±2.5% or ±0.25pF, whichever larger.																				
		Class2	J B	± 7.5 %																				
X5R	± 7.5 %																							
X6S	± 7.5 %																							
X7R	± 7.5 %																							
X7S	± 7.5 %																							
X7T	± 7.5 %																							
Q (Class1)	<table><tr><th>Rated Capacitance</th><th>Q</th></tr><tr><td>30pF and over</td><td>1,000 min.</td></tr><tr><td>Under 30pF</td><td>400+20xC min.</td></tr></table> C : Rated capacitance (pF)		Rated Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20xC min.																
Rated Capacitance	Q																							
30pF and over	1,000 min.																							
Under 30pF	400+20xC min.																							
D.F. (Class2)	Meet the initial spec.																							

(continued)

No.	Item		Performance		Test or inspection method		
14	Temperature cycle	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix1a or Appendix1b before testing.		
		Capacitance	Characteristics				
			Class1	C H C0G	±2.5% or ±0.25pF, whichever larger.		
					*Class2	J B	
			X5R	± 7.5 %			
			X6S	± 10 %			
		X7R	± 12.5 %				
		X7S					
		X7T					
		* Applied for some parts.					
Q (Class1)	Rated Capacitance		Q		Step	Temperature(°C)	Time (min.)
	30pF and over		1,000 min.		1	Min. operating temp. ± 3	30 ± 3
	Under 30pF		400+20×C min.		2	Reference Temp.	2 - 5
	C : Rated capacitance (pF)				3	Max. operating temp. ± 2	30 ± 2
D.F. (Class2)	Meet the initial spec.				4	Reference Temp.	2 - 5
Insulation Resistance	Meet the initial spec.						
Voltage proof	No insulation breakdown or other damage.						

(continued)

No.	Item		Performance		Test or inspection method														
15	Moisture Resistance (Steady State)	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b before testing. Leave at temperature 40 ± 2°C, 90 to 95%RH for 500 +24,0h. Leave the capacitors in ambient condition for 6 to 24h (Class1) or 24 ± 2h (Class2) before measurement.														
		Capacitance	<table><tr><td colspan="2">Characteristics</td><td>Change from the value before test</td></tr><tr><td>Class1</td><td>C H C0G</td><td>±5% or ±0.5pF, whichever larger.</td></tr><tr><td rowspan="4">*Class2</td><td>J B</td><td rowspan="4">± 10 % ± 12.5 % ± 25 %</td></tr><tr><td>X5R</td></tr><tr><td>X6S</td></tr><tr><td>X7R</td></tr><tr><td>X7S</td></tr><tr><td>X7T</td></tr></table>			Characteristics		Change from the value before test	Class1	C H C0G	±5% or ±0.5pF, whichever larger.	*Class2	J B	± 10 % ± 12.5 % ± 25 %	X5R	X6S	X7R	X7S	X7T
			Characteristics			Change from the value before test													
			Class1	C H C0G		±5% or ±0.5pF, whichever larger.													
			*Class2	J B		± 10 % ± 12.5 % ± 25 %													
		X5R																	
X6S																			
X7R																			
X7S																			
X7T																			
* Applied for some parts.																			
Q (Class1)	<table><tr><td>Rated Capacitance</td><td>Q</td></tr><tr><td>30pF and over</td><td>350 min.</td></tr><tr><td>10pF and over under 30pF</td><td>275+5/2×C min.</td></tr><tr><td>Under 10pF</td><td>200+10×C min.</td></tr></table>		Rated Capacitance	Q	30pF and over	350 min.	10pF and over under 30pF	275+5/2×C min.	Under 10pF	200+10×C min.									
	Rated Capacitance	Q																	
	30pF and over	350 min.																	
	10pF and over under 30pF	275+5/2×C min.																	
Under 10pF	200+10×C min.																		
C : Rated capacitance (pF)																			
D.F. (Class2)	200% of initial spec. max.																		
Insulation Resistance	1,000MΩ or 50MΩ·μF min. (As for the capacitors of rated voltage 16, 10V DC and lower, 1,000 MΩ or 10MΩ·μF min.,) whichever smaller.																		

(continued)

No.	Item		Performance		Test or inspection method																			
16	Moisture Resistance	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix1a or Appendix 1b before testing.																			
		Capacitance	<table><tr><td colspan="2">Characteristics</td><td>Change from the value before test</td></tr><tr><td>Class1</td><td>C H C0G</td><td>±7.5% or ±0.75pF, whichever larger.</td></tr><tr><td rowspan="4">*Class2</td><td>J B</td><td></td></tr><tr><td>X5R</td><td>± 10 %</td></tr><tr><td>X6S</td><td>± 12.5 %</td></tr><tr><td>X7R</td><td></td></tr><tr><td>X7S</td><td>± 25 %</td></tr><tr><td>X7T</td><td></td></tr></table>		Characteristics		Change from the value before test	Class1	C H C0G	±7.5% or ±0.75pF, whichever larger.	*Class2	J B		X5R	± 10 %	X6S	± 12.5 %	X7R		X7S	± 25 %	X7T		Apply the rated voltage at temperature 40±2°C and 90 to 95%RH for 500 +24,0h.
			Characteristics		Change from the value before test																			
			Class1	C H C0G	±7.5% or ±0.75pF, whichever larger.																			
			*Class2	J B																				
X5R	± 10 %																							
X6S	± 12.5 %																							
X7R																								
X7S	± 25 %																							
X7T																								
				Charge/discharge current shall not exceed 50mA.																				
				Leave the capacitors in ambient condition for 6 to 24h (Class1) or 24±2h (Class2) before measurement.																				

(continued)


No.	Item		Performance		Test or inspection method																		
17	Life	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix1a or Appendix 1b before testing.																		
		Capacitance	<table><tr><td colspan="2">Characteristics</td><td>Change from the value before test</td></tr><tr><td>Class1</td><td>C H C0G</td><td>±3% or ±0.3pF, whichever larger.</td></tr><tr><td rowspan="5">*Class2</td><td>J B</td><td></td></tr><tr><td>X5R</td><td>± 10 %</td></tr><tr><td>X6S</td><td>± 12.5 %</td></tr><tr><td>X7R</td><td></td></tr><tr><td>X7S</td><td>± 25 %</td></tr><tr><td>X7T</td><td></td></tr></table>		Characteristics		Change from the value before test	Class1	C H C0G	±3% or ±0.3pF, whichever larger.	*Class2	J B		X5R	± 10 %	X6S	± 12.5 %	X7R		X7S	± 25 %	X7T	
			Characteristics		Change from the value before test																		
			Class1	C H C0G	±3% or ±0.3pF, whichever larger.																		
			*Class2	J B																			
X5R	± 10 %																						
X6S	± 12.5 %																						
X7R																							
X7S	± 25 %																						
X7T																							
* Applied for some parts.																							
Q (Class1)	<table><tr><td>Rated Capacitance</td><td>Q</td></tr><tr><td>30pF and over</td><td>350 min.</td></tr><tr><td>10pF and over under 30pF</td><td>275+5/2×C min.</td></tr><tr><td>Under 10pF</td><td>200+10×C min.</td></tr></table>		Rated Capacitance	Q	30pF and over	350 min.	10pF and over under 30pF	275+5/2×C min.	Under 10pF	200+10×C min.													
Rated Capacitance	Q																						
30pF and over	350 min.																						
10pF and over under 30pF	275+5/2×C min.																						
Under 10pF	200+10×C min.																						
C : Rated capacitance (pF)																							
D.F. (Class2)	200% of initial spec. max.		For information which product has which applied voltage, please contact with our sales representative.																				
Insulation Resistance	1,000MΩ or 50MΩ·μF min. (As for the capacitors of rated voltage 16, 10V DC and lower, 1,000 MΩ or 10MΩ·μF min.,) whichever smaller.		Charge/discharge current shall not exceed 50mA.																				
				Leave the capacitors in ambient condition for 6 to 24h (Class1) or 24±2h (Class2) before measurement.																			
				Voltage conditioning (only for class 2) Voltage treat the capacitors under testing temperature and voltage for 1 hour.																			
				Leave the capacitors in ambient condition for 24±2h before measurement.																			
				Use this measurement for initial value.																			

*As for the initial measurement of capacitors (Class2) on number 8,12,13,14 and 15, leave capacitors at 150 -10,0°C for 1 hour and measure the value after leaving capacitors for 24 \pm 2h in ambient condition.

Appendix - 1a

P.C. Board for reliability test


Applied for C0402, C0603, C1005, C1608, C2012, C3216



Appendix - 1b

P.C. Board for reliability test


Applied for C3225, C4532, C5750



Appendix - 2a

P.C. Board for bending test


Applied for C0402, C0603, C1005



Appendix - 2b

P.C. Board for bending test



Applied for C1608, C2012, C3216, C3225, C4532, C5750



Material : Glass Epoxy (As per JIS C6484 GE4)


P.C. Board thickness : Appendix-2a 0.8mm

Appendix-1a, 1b, 2b 1.6mm

-  Copper (thickness 0.035mm)
-  Solder resist

TDK (EIA style)	Dimensions (mm)		
	a	b	c
C0402 (CC01005)	0.2	0.8	0.2
C0603 (CC0201)	0.3	0.8	0.3
C1005 (CC0402)	0.4	1.5	0.5
C1608 (CC0603)	1.0	3.0	1.2
C2012 (CC0805)	1.2	4.0	1.65
C3216 (CC1206)	2.2	5.0	2.0
C3225 (CC1210)	2.2	5.0	2.9
C4532 (CC1812)	3.5	7.0	3.7
C5750 (CC2220)	4.5	8.0	5.6

9. INSIDE STRUCTURE AND MATERIAL



No.	NAME	MATERIAL	
		Class1	Class2
1	Dielectric	CaZrO ₃	BaTiO ₃
2	Electrode	Nickel (Ni)	
3	Termination	Copper (Cu)	
4		Nickel (Ni)	
5		Tin (Sn)	

















10. RECOMMENDATION



As for C3225, C4532 and C5750 types, It is recommended to provide a slit (about 1mm wide) in the board under the components to improve washing Flux. And please make sure to dry detergent up completely before.







11. SOLDERING CONDITION




















As for C0402, C0603, C1005, C3225, C4532 and C5750 types, reflow soldering only.














12. Caution




No.	Process	Condition														
1	Operating Condition (Storage, Transportation)	<p>1-1. Storage</p> <p>1) The capacitors must be stored in an ambient temperature of 5 to 40°C with a relative humidity of 20 to 70%RH. The products should be used within 6 months upon receipt.</p> <p>2) The capacitors must be operated and stored in an environment free of dew condensation and these gases such as Hydrogen Sulphide, Hydrogen Sulphate, Chlorine, Ammonia and sulfur.</p> <p>3) Avoid storing in sun light and falling of dew.</p> <p>4) Do not use capacitors under high humidity and high and low atmospheric pressure which may affect capacitors reliability.</p> <p>5) Capacitors should be tested for the solderability when they are stored for long time.</p> <p>1-2. Handling in transportation</p> <p>In case of the transportation of the capacitors, the performance of the capacitors may be deteriorated depending on the transportation condition. (Refer to JEITA RCR-2335C 9.2 Handling in transportation)</p>														
2	Circuit design  Caution	<p>2-1. Operating temperature</p> <p>Operating temperature should be followed strictly within this specification, especially be careful with maximum temperature.</p> <p>1) Do not use capacitors above the maximum allowable operating temperature.</p> <p>2) Surface temperature including self heating should be below maximum operating temperature. (Due to dielectric loss, capacitors will heat itself when AC is applied. Especially at high frequencies around its SRF, the heat might be so extreme that it may damage itself or the product mounted on. Please design the circuit so that the maximum temperature of the capacitors including the self heating to be below the maximum allowable operating temperature. Temperature rise at capacitor surface shall be below 20°C)</p> <p>3) The electrical characteristics of the capacitors will vary depending on the temperature. The capacitors should be selected and designed in taking the temperature into consideration.</p> <p>2-2 Operating voltage</p> <p>1) Operating voltage across the terminals should be below the rated voltage. When AC and DC are super imposed, V_{0-P} must be below the rated voltage. _____ (1) and (2) AC or pulse with overshooting, V_{P-P} must be below the rated voltage. _____ (3), (4) and (5) When the voltage is started to apply to the circuit or it is stopped applying, the irregular voltage may be generated for a transit period because of resonance or switching. Be sure to use the capacitors within rated voltage containing these Irregular voltage.</p> <table><tr><th>Voltage</th><th>(1) DC voltage</th><th>(2) DC + AC voltage</th><th>(3) AC voltage</th></tr><tr><td>Positional Measurement (Rated voltage)</td><td></td><td></td><td></td></tr></table> <table><tr><th>Voltage</th><th>(4) Pulse voltage (A)</th><th>(5) Pulse voltage (B)</th></tr><tr><td>Positional Measurement (Rated voltage)</td><td></td><td></td></tr></table>	Voltage	(1) DC voltage	(2) DC + AC voltage	(3) AC voltage	Positional Measurement (Rated voltage)				Voltage	(4) Pulse voltage (A)	(5) Pulse voltage (B)	Positional Measurement (Rated voltage)		
Voltage	(1) DC voltage	(2) DC + AC voltage	(3) AC voltage													
Positional Measurement (Rated voltage)																
Voltage	(4) Pulse voltage (A)	(5) Pulse voltage (B)														
Positional Measurement (Rated voltage)																




No.	Process	Condition																																																												
2	Circuit design  Caution	<p>2) Even below the rated voltage, if repetitive high frequency AC or pulse is applied, the reliability of the capacitors may be reduced.</p> <p>3) The effective capacitance will vary depending on applied DC and AC voltages. The capacitors should be selected and designed in taking the voltages into consideration.</p> <p>2-3. Frequency</p> <p>When the capacitors (Class 2) are used in AC and/or pulse voltages, the capacitors may vibrate themselves and generate audible sound.</p>																																																												
3	Designing P.C. board	<p>The amount of solder at the terminations has a direct effect on the reliability of the capacitors.</p> <p>1) The greater the amount of solder, the higher the stress on the chip capacitor, and the more likely that it will break. When designing a P.C. board, determine the shape and size of the solder lands to have proper amount of solder on the terminations.</p> <p>2) Avoid using common solder land for multiple terminations and provide individual solder land for each terminations.</p> <p>3) Size and recommended land dimensions.</p> <div></div> <p>• Flow soldering (mm)</p> <table><tr><th>Type Symbol</th><th>C1608 (CC0603)</th><th>C2012 (CC0805)</th><th>C3216 (CC1206)</th></tr><tr><td>A</td><td>0.7 - 1.0</td><td>1.0 - 1.3</td><td>2.1 - 2.5</td></tr><tr><td>B</td><td>0.8 - 1.0</td><td>1.0 - 1.2</td><td>1.1 - 1.3</td></tr><tr><td>C</td><td>0.6 - 0.8</td><td>0.8 - 1.1</td><td>1.0 - 1.3</td></tr></table> <p>• Reflow soldering (mm)</p> <table><tr><th>Type Symbol</th><th>C0402 (CC01005)</th><th>C0603 (CC0201)</th><th>C1005 (CC0402)</th><th>C1608 (CC0603)</th><th>C2012 (CC0805)</th></tr><tr><td>A</td><td>0.15 - 0.25</td><td>0.25 - 0.35</td><td>0.3 - 0.5</td><td>0.6 - 0.8</td><td>0.9 - 1.2</td></tr><tr><td>B</td><td>0.15 - 0.25</td><td>0.2 - 0.3</td><td>0.35 - 0.45</td><td>0.6 - 0.8</td><td>0.7 - 0.9</td></tr><tr><td>C</td><td>0.15 - 0.25</td><td>0.25 - 0.35</td><td>0.4 - 0.6</td><td>0.6 - 0.8</td><td>0.9 - 1.2</td></tr></table> <table><tr><th>Type Symbol</th><th>C3216 (CC1206)</th><th>C3225 (CC1210)</th><th>C4532 (CC1812)</th><th>C5750 (CC2220)</th></tr><tr><td>A</td><td>2.0 - 2.4</td><td>2.0 - 2.4</td><td>3.1 - 3.7</td><td>4.1 - 4.8</td></tr><tr><td>B</td><td>1.0 - 1.2</td><td>1.0 - 1.2</td><td>1.2 - 1.4</td><td>1.2 - 1.4</td></tr><tr><td>C</td><td>1.1 - 1.6</td><td>1.9 - 2.5</td><td>2.4 - 3.2</td><td>4.0 - 5.0</td></tr></table>	Type Symbol	C1608 (CC0603)	C2012 (CC0805)	C3216 (CC1206)	A	0.7 - 1.0	1.0 - 1.3	2.1 - 2.5	B	0.8 - 1.0	1.0 - 1.2	1.1 - 1.3	C	0.6 - 0.8	0.8 - 1.1	1.0 - 1.3	Type Symbol	C0402 (CC01005)	C0603 (CC0201)	C1005 (CC0402)	C1608 (CC0603)	C2012 (CC0805)	A	0.15 - 0.25	0.25 - 0.35	0.3 - 0.5	0.6 - 0.8	0.9 - 1.2	B	0.15 - 0.25	0.2 - 0.3	0.35 - 0.45	0.6 - 0.8	0.7 - 0.9	C	0.15 - 0.25	0.25 - 0.35	0.4 - 0.6	0.6 - 0.8	0.9 - 1.2	Type Symbol	C3216 (CC1206)	C3225 (CC1210)	C4532 (CC1812)	C5750 (CC2220)	A	2.0 - 2.4	2.0 - 2.4	3.1 - 3.7	4.1 - 4.8	B	1.0 - 1.2	1.0 - 1.2	1.2 - 1.4	1.2 - 1.4	C	1.1 - 1.6	1.9 - 2.5	2.4 - 3.2	4.0 - 5.0
Type Symbol	C1608 (CC0603)	C2012 (CC0805)	C3216 (CC1206)																																																											
A	0.7 - 1.0	1.0 - 1.3	2.1 - 2.5																																																											
B	0.8 - 1.0	1.0 - 1.2	1.1 - 1.3																																																											
C	0.6 - 0.8	0.8 - 1.1	1.0 - 1.3																																																											
Type Symbol	C0402 (CC01005)	C0603 (CC0201)	C1005 (CC0402)	C1608 (CC0603)	C2012 (CC0805)																																																									
A	0.15 - 0.25	0.25 - 0.35	0.3 - 0.5	0.6 - 0.8	0.9 - 1.2																																																									
B	0.15 - 0.25	0.2 - 0.3	0.35 - 0.45	0.6 - 0.8	0.7 - 0.9																																																									
C	0.15 - 0.25	0.25 - 0.35	0.4 - 0.6	0.6 - 0.8	0.9 - 1.2																																																									
Type Symbol	C3216 (CC1206)	C3225 (CC1210)	C4532 (CC1812)	C5750 (CC2220)																																																										
A	2.0 - 2.4	2.0 - 2.4	3.1 - 3.7	4.1 - 4.8																																																										
B	1.0 - 1.2	1.0 - 1.2	1.2 - 1.4	1.2 - 1.4																																																										
C	1.1 - 1.6	1.9 - 2.5	2.4 - 3.2	4.0 - 5.0																																																										


No.	Process	Condition	
3	Designing P.C.board	4) Recommended chip capacitor layout is as following.	
		Disadvantage against bending stress	Advantage against bending stress
		Perforation or slit	Perforation or slit
Mounting face		 <p>Break P.C.board with mounted side up.</p>	 <p>Break P.C.board with mounted side down.</p>
		Mount perpendicularly to perforation or slit	Mount in parallel with perforation or slit
		Perforation or slit	Perforation or slit
Chip arrangement (Direction)			
		Closer to slit is higher stress	Away from slit is less stress
		Distance from slit	Distance from slit
		 <p>$(L_1 < L_2)$</p>	 <p>$(L_1 < L_2)$</p>

No.	Process	Condition												
3	Designing P.C.board	<div>5) Mechanical stress varies according to location of chip capacitors on the P.C.board.</div> <div></div> <div>The stress in capacitors is in the following order. A > B = C > D > E</div> <div>6) Layout recommendation</div> <table><tr><th>Example</th><th>Use of common solder land</th><th>Soldering with chassis</th><th>Use of common solder land with other SMD</th></tr><tr><td>Need to avoid</td><td></td><td></td><td></td></tr><tr><td>Recommendation</td><td></td><td></td><td></td></tr></table>	Example	Use of common solder land	Soldering with chassis	Use of common solder land with other SMD	Need to avoid				Recommendation			
Example	Use of common solder land	Soldering with chassis	Use of common solder land with other SMD											
Need to avoid														
Recommendation														










No.	Process	Condition															
4	Mounting	<div>4-1. Stress from mounting head</div> <div>If the mounting head is adjusted too low, it may induce excessive stress in the chip capacitor to result in cracking. Please take following precautions.</div> <div>1) Adjust the bottom dead center of the mounting head to reach on the P.C.board surface and not press it.</div> <div>2) Adjust the mounting head pressure to be 1 to 3N of static weight.</div> <div>3) To minimize the impact energy from mounting head, it is important to provide support from the bottom side of the P.C.board.</div> <div>See following examples.</div> <table><tr><th></th><th>Not recommended</th><th>Recommended</th></tr><tr><td>Single sided mounting</td><td></td><td></td></tr><tr><td>Double-si des mounting</td><td></td><td></td></tr></table> <div>When the centering jaw is worn out, it may give mechanical impact on the capacitors to cause crack. Please control the close up dimension of the centering jaw and provide sufficient preventive maintenance and replacement of it.</div> <div>4-2. Amount of adhesive</div> <div></div> <div>Example : C2012 (CC0805), C3216 (CC1206)</div> <table><tr><td>a</td><td>0.2mm min.</td></tr><tr><td>b</td><td>70 - 100μm</td></tr><tr><td>c</td><td>Do not touch the solder land</td></tr></table>		Not recommended	Recommended	Single sided mounting			Double-si des mounting			a	0.2mm min.	b	70 - 100μm	c	Do not touch the solder land
	Not recommended	Recommended															
Single sided mounting																	
Double-si des mounting																	
a	0.2mm min.																
b	70 - 100μm																
c	Do not touch the solder land																






















No.	Process	Condition																			
5	Soldering	<div>5-1. Flux selection</div> <div>Although highly-activated flux gives better solderability, substances which increase activity may also degrade the insulation of the chip capacitors.</div> <div>To avoid such degradation, it is recommended following.</div> <div><div>1) It is recommended to use a mildly activated rosin flux (less than 0.1wt% chlorine).</div><div>Strong flux is not recommended.</div><div>2) Excessive flux must be avoided. Please provide proper amount of flux.</div><div>3) When water-soluble flux is used, enough washing is necessary.</div></div> <div>5-2. Recommended soldering profile by various methods</div> <div><div><div>Wave soldering</div></div><div><div>Reflow soldering</div></div></div> <div><div>Manual soldering (Solder iron)</div></div> <div><div>APPLICATION</div><div>As for C1608, C2012 and C3216 applied to wave soldering and reflow soldering.</div><div>As for C0402, C0603, C1005, C3225, C4532, C5750 applied only to reflow soldering.</div></div> <div><div>*As for peak temperature of manual soldering, please refer“5-6. Solder repair by solder iron”</div></div> <div>5-3. Recommended soldering peak temp and peak temp duration</div> <table><tr><th rowspan="2"></th><th colspan="2">Wave soldering</th><th colspan="2">Reflow soldering</th></tr><tr><th>Peak temp(°C)</th><th>Duration(sec.)</th><th>Peak temp(°C)</th><th>Duration(sec.)</th></tr><tr><td>Sn-Pb Solder</td><td>250 max.</td><td>3 max.</td><td>230 max.</td><td>20 max.</td></tr><tr><td>Lead Free Solder</td><td>260 max.</td><td>5 max.</td><td>260 max.</td><td>10 max.</td></tr></table> <div>Recommended solder compositions</div> <div>Sn-37Pb (Sn-Pb solder)</div> <div>Sn-3.0Ag-0.5Cu (Lead Free Solder)</div>		Wave soldering		Reflow soldering		Peak temp(°C)	Duration(sec.)	Peak temp(°C)	Duration(sec.)	Sn-Pb Solder	250 max.	3 max.	230 max.	20 max.	Lead Free Solder	260 max.	5 max.	260 max.	10 max.
	Wave soldering			Reflow soldering																	
	Peak temp(°C)	Duration(sec.)	Peak temp(°C)	Duration(sec.)																	
Sn-Pb Solder	250 max.	3 max.	230 max.	20 max.																	
Lead Free Solder	260 max.	5 max.	260 max.	10 max.																	



No.	Process	Condition																
5	Soldering	5-4. Avoiding thermal shock																
		1) Preheating condition																
		<table><tr><th>Soldering</th><th>Type</th><th>Temp. (°C)</th></tr><tr><td>Wave soldering</td><td>C1608, C2012, C3216</td><td>$\Delta T \leq 150$</td></tr><tr><td rowspan="2">Reflow soldering</td><td>C0402, C0603, C1005, C1608, C2012, C3216</td><td>$\Delta T \leq 150$</td></tr><tr><td>C3225, C4532, C5750</td><td>$\Delta T \leq 130$</td></tr><tr><td rowspan="2">Manual soldering</td><td>C0402, C0603, C1005, C1608, C2012, C3216</td><td>$\Delta T \leq 150$</td></tr><tr><td>C3225, C4532, C5750</td><td>$\Delta T \leq 130$</td></tr></table>	Soldering	Type	Temp. (°C)	Wave soldering	C1608, C2012, C3216	$\Delta T \leq 150$	Reflow soldering	C0402, C0603, C1005, C1608, C2012, C3216	$\Delta T \leq 150$	C3225, C4532, C5750	$\Delta T \leq 130$	Manual soldering	C0402, C0603, C1005, C1608, C2012, C3216	$\Delta T \leq 150$	C3225, C4532, C5750	$\Delta T \leq 130$
		Soldering	Type	Temp. (°C)														
		Wave soldering	C1608, C2012, C3216	$\Delta T \leq 150$														
		Reflow soldering	C0402, C0603, C1005, C1608, C2012, C3216	$\Delta T \leq 150$														
			C3225, C4532, C5750	$\Delta T \leq 130$														
		Manual soldering	C0402, C0603, C1005, C1608, C2012, C3216	$\Delta T \leq 150$														
			C3225, C4532, C5750	$\Delta T \leq 130$														
		2) Cooling condition																
Natural cooling using air is recommended. If the chips are dipped into a solvent for cleaning, the temperature difference (ΔT) must be less than 100°C.																		
5-5. Amount of solder																		
Excessive solder will induce higher tensile force in chip capacitors when temperature changes and it may result in chip cracking. In sufficient solder may detach the capacitors from the P.C.board.																		
<div><div>Excessive solder</div><div></div><div>Higher tensile force in chip capacitor to cause crack</div></div>																		
<div><div>Adequate</div><div></div><div></div></div>																		
<div><div>Insufficient solder</div><div></div><div>Low robustness may cause contact failure or chip capacitor comes off the P.C.board.</div></div>																		
5-6. Solder repair by solder iron																		
1) Selection of the soldering iron tip																		
Tip temperature of solder iron varies by its type, P.C.board material and solder land size. The higher the tip temperature, the quicker the operation. However, heat shock may cause a crack in the chip capacitors. Please make sure the tip temp. before soldering and keep the peak temp and time in accordance with following recommended condition. (Please preheat the chip capacitors with the condition in 5-4 to avoid the thermal shock.)																		
Recommended solder iron condition (Sn-Pb Solder and Lead Free Solder)																		
<table><tr><th>Type</th><th>Temp. (°C)</th><th>Wattage (W)</th><th>Shape (mm)</th></tr><tr><td>C0603(CC0201) C1005(CC0402) C1608(CC0603) C2012(CC0805) C3216(CC1206)</td><td>350 max.</td><td rowspan="2">20 max.</td><td rowspan="2">ϕ 3.0 max.</td></tr><tr><td>C3225(CC1210) C4520(CC1808) C4532(CC1812) C5750(CC2220)</td><td>280 max.</td></tr></table>		Type	Temp. (°C)	Wattage (W)	Shape (mm)	C0603(CC0201) C1005(CC0402) C1608(CC0603) C2012(CC0805) C3216(CC1206)	350 max.	20 max.	ϕ 3.0 max.	C3225(CC1210) C4520(CC1808) C4532(CC1812) C5750(CC2220)	280 max.							
Type	Temp. (°C)	Wattage (W)	Shape (mm)															
C0603(CC0201) C1005(CC0402) C1608(CC0603) C2012(CC0805) C3216(CC1206)	350 max.	20 max.	ϕ 3.0 max.															
C3225(CC1210) C4520(CC1808) C4532(CC1812) C5750(CC2220)	280 max.																	


No.	Process	Condition												
5	Soldering	<div>2) Direct contact of the soldering iron with ceramic dielectric of chip capacitors may cause crack. Do not touch the ceramic dielectric and the terminations by solder iron.</div> <div>3) It is not recommended to reuse dismounted capacitors. (For soft electrode)</div> <div>5-7.Soldering rework using spot heater Heat stress during rework may possibly be reduced by using a spot heater (also called a “blower”) rather than a soldering iron. It is applied only to adding solder in the case of insufficient solder amount.</div> <div>1) Reworking using a spot heater may suppress the occurrence of cracks in the capacitor compared to using a soldering iron. A spot heater can heat up a capacitor uniformly with a small heat gradient which leads to lower thermal stress caused by quick heating and cooling or localized heating. Moreover, where ultra-small capacitors are mounted close together on a printed circuit board, reworking with a spot heater can eliminate the risk of direct contact between the tip of a soldering iron and a capacitor.</div> <div>2) Rework condition If the blower nozzle of a spot heater is too close to a capacitor, a crack in the capacitor may occur due to heat stress. Below are recommendations for avoiding such an occurrence. Keep more than 5mm between a capacitor and a spot heater nozzle. The blower temperature of the spot theater shall be lower than 400°C. The airflow shall be set as weak as possible. The diameter of the nozzle is recommended to be 2mm(one-outlet type).The size is standard and common. Duration of blowing hot air is recommended to be 10s or less C1608(CC0603), C2012(CC0805), C3216(CC1206) and 30s or less for C3225(CC1210), C4520(CC1808), C4532(CC1812) and C5750(CC2220), considering surface area of the capacitor and melting temperature of solder. The angle between the nozzle and the capacitor is recommended to be 45degrees in order to work easily and to avoid partial area heating. As is the case when using a soldering iron, preheating reduces thermal stress on capacitors and improves operating efficiency.</div> <div>• Recommended rework condition (Consult the component manufactures for details.)</div> <table><tr><td>Distance from nozzle</td><td>5mm and over</td></tr><tr><td>Nozzle angle</td><td>45degrees</td></tr><tr><td>Nozzle temp.</td><td>400°C and less</td></tr><tr><td>Airflow</td><td>Set as weak as possible (The airflow shall be the minimum value necessary for solder to melt in the Conditions mentioned above.)</td></tr><tr><td>Nozzle diameter</td><td>φ 2mm (one-outlet type)</td></tr><tr><td>Blowing duration</td><td>10s and less (C1608[CC0603], C2012[CC0805], C3216[CC1206]) 30s and less (C3225[CC1210], C4532[CC1812], C5750[CC2220])</td></tr></table> <div>• Example of recommended spot heater use</div> <div><p>One-outlet type nozzle</p><p>Angle : 45degrees</p></div>	Distance from nozzle	5mm and over	Nozzle angle	45degrees	Nozzle temp.	400°C and less	Airflow	Set as weak as possible (The airflow shall be the minimum value necessary for solder to melt in the Conditions mentioned above.)	Nozzle diameter	φ 2mm (one-outlet type)	Blowing duration	10s and less (C1608[CC0603], C2012[CC0805], C3216[CC1206]) 30s and less (C3225[CC1210], C4532[CC1812], C5750[CC2220])
Distance from nozzle	5mm and over													
Nozzle angle	45degrees													
Nozzle temp.	400°C and less													
Airflow	Set as weak as possible (The airflow shall be the minimum value necessary for solder to melt in the Conditions mentioned above.)													
Nozzle diameter	φ 2mm (one-outlet type)													
Blowing duration	10s and less (C1608[CC0603], C2012[CC0805], C3216[CC1206]) 30s and less (C3225[CC1210], C4532[CC1812], C5750[CC2220])													

No.	Process	Condition
5	Soldering	<p>3) Amount of solder should be suitable to form a proper fillet shape. Excess solder causes mechanical and thermal stress on a capacitor and results in cracks. Insufficient solder causes weak adherence of the capacitor to the substrate and may result in detachment of a capacitor and deteriorate reliability of the printed wiring board. See the example of appropriate solder fillet shape for 5-5.Amount of solder.</p> <p>5-8. Sn-Zn solder Sn-Zn solder affects product reliability. Please contact TDK in advance when utilize Sn-Zn solder.</p> <p>5-9. Countermeasure for tombstone The misalignment between the mounted positions of the capacitors and the land patterns should be minimized. The tombstone phenomenon may occur especially the capacitors are mounted (in longitudinal direction) in the same direction of the reflow soldering. (Refer to JEITA RCR-2335C Annex A (Informative) Recommendations to prevent the tombstone phenomenon)</p>
6	Cleaning	<p>1) If an unsuitable cleaning fluid is used, flux residue or some foreign articles may stick to chip capacitors surface to deteriorate especially the insulation resistance.</p> <p>2) If cleaning condition is not suitable, it may damage the chip capacitors.</p> <p>2)-1. Insufficient washing (1) Terminal electrodes may corrode by Halogen in the flux. (2) Halogen in the flux may adhere on the surface of capacitors, and lower the insulation resistance. (3) Water soluble flux has higher tendency to have above mentioned problems (1) and (2).</p> <p>2)-2. Excessive washing When ultrasonic cleaning is used, excessively high ultrasonic energy output can affect the connection between the ceramic chip capacitor's body and the terminal electrode. To avoid this, following is the recommended condition. Power : 20W/□max. Frequency : 40kHz max. Washing time : 5 minutes max.</p> <p>2)-3. If the cleaning fluid is contaminated, density of Halogen increases, and it may bring the same result as insufficient cleaning.</p>

No.	Process	Condition				
7	Coating and molding of the P.C. board	<div>1) When the P.C. board is coated, please verify the quality influence on the product.</div> <div>2) Please verify carefully that there is no harmful decomposing or reaction gas emission during curing which may damage the chip capacitors.</div> <div>3) Please verify the curing temperature.</div>				
8	Handling after chip mounted <div><div>!</div> Caution</div>	<div>1) Please pay attention not to bend or distort the P.C.board after soldering in handling otherwise the chip capacitors may crack.</div> <div><div><div>Bend</div></div><div><div>Twist</div></div></div> <div>2) Printed circuit board cropping should not be carried out by hand, but by using the proper tooling. Printed circuit board cropping should be carried out using a board cropping jig as shown in the following figure or a board cropping apparatus to prevent inducing mechanical stress on the board.</div> <div>(1)Example of a board cropping jig</div> <div>Recommended example: The board should be pushed from the back side, close to the cropping jig so that the board is not bent and the stress applied to the capacitor is compressive.</div> <div>Unrecommended example: If the pushing point is far from the cropping jig and the pushing direction is from the front side of the board, large tensile stress is applied to the capacitor, which may cause cracks.</div> <div><div><div>Outline of jig</div></div><div><table><tr><th>Recommended</th><th>Unrecommended</th></tr><tr><td></td><td></td></tr></table></div></div>	Recommended	Unrecommended		
Recommended	Unrecommended					
						

No.	Process	Condition																	
8	Handling after chip mounted ⚠ Caution	<div><div>(2)Example of a board cropping machine</div><div>An outline of a printed circuit board cropping machine is shown below. The top and bottom blades are aligned with one another along the lines with the V-grooves on printed circuit board when cropping the board. Unrecommended example: Misalignment of blade position between top and bottom, right and left, or front and rear blades may cause a crack in the capacitor.</div><div><div><div>Outline of machine</div><div></div></div><div><div><div>Principle of operation</div><div></div></div><div><div><div>Cross-section diagram</div><div></div></div></div><div><table><tr><th rowspan="2">Recommended</th><th colspan="3">Unrecommended</th></tr><tr><th>Top-bottom misalignment</th><th>Left-right misalignment</th><th>Front-rear misalignment</th></tr><tr><td><div><div>Top blade</div><div></div><div>Board</div><div>Bottom blade</div></div></td><td><div><div>Top blade</div><div></div><div>Bottom blade</div></div></td><td><div><div>Top blade</div><div></div><div>Bottom blade</div></div></td><td><div><div>Top blade</div><div></div><div>Bottom blade</div></div></td></tr></table></div><div><div>3) When functional check of the P.C.board is performed, check pin pressure tends to be adjusted higher for fear of loose contact. But if the pressure is excessive and bend the P.C.board, it may crack the chip capacitors or peel the terminations off. Please adjust the check pins not to bend the P.C.board.</div><div><table><tr><th>Item</th><th>Not recommended</th><th>Recommended</th></tr><tr><td>Board bending</td><td><div></div></td><td><div></div></td></tr></table></div></div></div></div></div>	Recommended	Unrecommended			Top-bottom misalignment	Left-right misalignment	Front-rear misalignment	<div><div>Top blade</div><div></div><div>Board</div><div>Bottom blade</div></div>	<div><div>Top blade</div><div></div><div>Bottom blade</div></div>	<div><div>Top blade</div><div></div><div>Bottom blade</div></div>	<div><div>Top blade</div><div></div><div>Bottom blade</div></div>	Item	Not recommended	Recommended	Board bending	<div></div>	<div></div>
Recommended	Unrecommended																		
	Top-bottom misalignment	Left-right misalignment	Front-rear misalignment																
<div><div>Top blade</div><div></div><div>Board</div><div>Bottom blade</div></div>	<div><div>Top blade</div><div></div><div>Bottom blade</div></div>	<div><div>Top blade</div><div></div><div>Bottom blade</div></div>	<div><div>Top blade</div><div></div><div>Bottom blade</div></div>																
Item	Not recommended	Recommended																	
Board bending	<div></div>	<div></div>																	

No.	Process	Condition
9	Handling of loose chip capacitors	<p>1) If dropped the chip capacitors may crack. Once dropped do not use it. Especially, the large case sized chip capacitors are tendency to have cracks easily, so please handle with care.</p>  <p>2) Piling the P.C.board after mounting for storage or handling, the corner of the P.C. board may hit the chip capacitors of another board to cause crack.</p> 
10	Capacitance aging	The capacitors (Class 2) have aging in the capacitance. They may not be used in precision time constant circuit. In case of the time constant circuit, the evaluation should be done well.
11	Estimated life and estimated failure rate of capacitors	<p>As per the estimated life and the estimated failure rate depend on the temperature and the voltage. This can be calculated by the equation described in JEITA RCR-2335C Annex F(Informative) Calculation of the estimated lifetime and the estimated failure rate (Voltage acceleration coefficient : 3 multiplication rule, Temperature acceleration coefficient : 10°C rule)</p> <p>The failure rate can be decreased by reducing the temperature and the voltage but they will not be guaranteed.</p>

No.	Process	Condition
12	Caution during operation of equipment	<p>1) A capacitor shall not be touched directly with bare hands during operation in order to avoid electric shock. Electric energy held by the capacitor may be discharged through the human body when touched with a bare hand. Even when the equipment is off, a capacitor may stay charged. The capacitor should be handled after being completely discharged using a resistor.</p> <p>2) The terminals of a capacitor shall not be short-circuited by any accidental contact with a conductive object. A capacitor shall not be exposed to a conductive liquid such as an acid or alkali solution. A conductive object or liquid, such as acid and alkali, between the terminals may lead to the breakdown of a capacitor due to short circuit</p> <p>3) Confirm that the environment to which the equipment will be exposed during transportation and operation meets the specified conditions. Do not to use the equipment in the following environments. (1) Environment where a capacitor is splattered with water or oil (2) Environment where a capacitor is exposed to direct sunlight (3) Environment where a capacitor is exposed to Ozone, ultraviolet rays or radiation (4) Environment where a capacitor exposed to corrosive gas(e.g. hydrogen sulfide, sulfur dioxide, chlorine. ammonia gas etc.) (5) Environment where a capacitor exposed to vibration or mechanical shock exceeding the specified limits. (6) Atmosphere change with causes condensation</p>
13	 Others Caution	<p>The products listed on this specification sheet are intended for use in general electronic equipment (AV equipment, telecommunications equipment, home appliances, amusement equipment, computer equipment, personal equipment, office equipment, measurement equipment, industrial robots) under a normal operation and use condition.</p> <p>The products are not designed or warranted to meet the requirements of the applications listed below, whose performance and/or quality require a more stringent level of safety or reliability, or whose failure, malfunction or trouble could cause serious damage to society, person or property. Please understand that we are not responsible for any damage or liability caused by use of the products in any of the applications below or for any other use exceeding the range or conditions set forth in this specification sheet. If you intend to use the products in the applications listed below or if you have special requirements exceeding the range or conditions set forth in this specification, please contact us.</p> <p>(1) Aerospace/Aviation equipment (2) Transportation equipment (cars, electric trains, ships, etc.) (3) Medical equipment (Excepting Pharmaceutical Affairs Law classification Class1, 2) (4) Power-generation control equipment (5) Atomic energy-related equipment (6) Seabed equipment (7) Transportation control equipment (8) Public information-processing equipment (9) Military equipment (10) Electric heating apparatus, burning equipment (11) Disaster prevention/crime prevention equipment (12) Safety equipment (13) Other applications that are not considered general-purpose applications</p> <p>When designing your equipment even for general-purpose applications, you are kindly requested to take into consideration securing protection circuit/device or providing backup circuits in your equipment.</p>

13. Packaging label

Packaging shall be done to protect the components from the damage during transportation and storing, and a label which has the following information shall be attached.

- 1) Inspection No.
- 2) TDK P/N
- 3) Customer's P/N
- 4) Quantity

*Composition of Inspection No.

Example F 2 A – 00 – 000
 (a) (b) (c) (d) (e)

- a) Line code
- b) Last digit of the year
- c) Month and A for January and B for February and so on. (Skip I)
- d) Inspection Date of the month.
- e) Serial No. of the day

14. Bulk packaging quantity

Total number of components in a plastic bag for bulk packaging: 1,000pcs.
As for C0402, C0603 and C1005 types, not available for bulk packaging.

15. TAPE PACKAGING SPECIFICATION


1. CONSTRUCTION AND DIMENSION OF TAPING

1-1. Dimensions of carrier tape

Dimensions of paper tape shall be according to Appendix 3, 4.

Dimensions of plastic tape shall be according to Appendix 5, 6.

1-2. Bulk part and leader of taping




1-3. Dimensions of reel

Dimensions of Ø178 reel shall be according to Appendix 7, 8.

Dimensions of Ø330 reel shall be according to Appendix 9, 10.

1-4. Structure of taping




2. CHIP QUANTITY

Type	Thickness of chip	Taping Material	Chip quantity (pcs.)	
			φ178mm reel	φ330mm reel
C0402	0.20 mm	Paper	20,000	-
C0603	0.30 mm	Paper	15,000	-
C1005	0.50 mm	Paper	10,000	50,000
C1608	0.80 mm	Paper	4,000	10,000
C2012	0.60 mm	Paper	4,000	10,000
	0.85 mm	Paper or Plastic		
	1.25 mm	Plastic	2,000	
C3216	0.60 mm	Paper	4,000	10,000
	0.85 mm	Paper or Plastic		
	1.15 mm	Plastic	2,000	
	1.30 mm			
	1.60 mm			8,000
C3225	1.15 mm	Plastic	2,000	10,000
	1.25 mm		2,000	8,000
	1.30 mm			
	1.60 mm			
	2.00 mm		1,000	5,000
	2.30 mm			
	2.50 mm			
C4532	1.60 mm	Plastic	1,000	3,000
	2.00 mm		500	
	2.30 mm			
	2.50 mm			
	2.80 mm			2,000
	3.20 mm			
C5750	2.00 mm	Plastic	500	3,000
	2.30 mm			
	2.50 mm			
	2.80 mm			2,000

3. PERFORMANCE SPECIFICATIONS

3-1. Fixing peeling strength (top tape)

0.05-0.7N. (See the following figure.)




3-2. Carrier tape shall be flexible enough to be wound around a minimum radius of 30mm with components in tape.

3-3. The missing of components shall be less than 0.1%

3-4. Components shall not stick to fixing tape.

3-5. The fixing tapes shall not protrude beyond the edges of the carrier tape
not shall cover the sprocket holes.

Appendix 3



Symbol Type	A	B	C	D	E	F
C0402 (C01005)	(0.25)	(0.45)	8.00 ± 0.30	3.50 ± 0.05	1.75 ± 0.10	2.00 ± 0.05
C0603 (CC0201)	(0.38)	(0.68)				
C1005 (CC0402)	(0.65) * ₁ (0.73) * ₂ (0.80)	(1.15) * ₁ (1.23) * ₂ (1.30)				

Symbol Type	G	H	J	T
C0402 (C01005)	2.00 ± 0.05	4.00 ± 0.10	Ø 1.5 ^{+0.10} ₀	0.29 min.
C0603 (CC0201)				0.40 min.
C1005 (CC0402)				0.60± 0.05 * ₁ 0.68± 0.05 * ₂ 0.75± 0.05


* The values in the parentheses () are for reference.

*₁ Applied to thickness, 0.5 ± 0.10 mm and $0.50 + 0.15 / - 0.10$ mm products.

*₂ Applied to thickness, $0.50 + 0.20 / - 0.10$ mm products.

Appendix 4

Paper Tape



(Unit : mm)


Symbol Type	A	B	C	D	E	F
C1608 (CC0603)	(1.10)	(1.90)	8.00 ± 0.30	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10
C2012 (CC0805)	(1.50)	(2.30)				
C3216 (CC1206)	(1.90)	(3.50)				

Symbol Type	G	H	J	T
C1608 (CC0603)	2.00 ± 0.05	4.00 ± 0.10	Ø 1.5 ^{+0.10} ₀	1.20max.
C2012 (CC0805)				
C3216 (CC1206)				

* The values in the parentheses () are for reference.

Appendix 5

Plastic Tape



(Unit : mm)

Symbol Type	A	B	C	D	E	F
C2012 (CC0805)	(1.50)	(2.30)	8.00 ± 0.30 [12.0 ± 0.30]	3.50 ± 0.05 [5.50 ± 0.05]	1.75 ± 0.10	4.00 ± 0.10
C3216 (CC1206)	(1.90)	(3.50)				
C3225 (CC1210)	(2.90)	(3.60)				
Symbol Type	G	H	J	K	t	Q
C2012 (CC0805)	2.00 ± 0.05	4.00 ± 0.10	Ø 1.5 $\begin{smallmatrix} +0.10 \\ 0 \end{smallmatrix}$	3.20max.	0.60max.	Ø 0.50 min.
C3216 (CC1206)						
C3225 (CC1210)						


* The values in the parentheses () are for reference.

* As for 2.5mm thickness products, apply values in the brackets [].

* Exceptionally no hole in the cavity is applied. Please inquire if hole in cavity is mandatory.

Appendix 6

Plastic Tape




(Unit : mm)

Symbol Type	A	B	C	D	E	F
C4532 (CC1812)	(3.60)	(4.90)	12.0 ± 0.30	5.50 ± 0.05	1.75 ± 0.10	8.00 ± 0.10
C5750 (CC2220)	(5.40)	(6.10)				
Symbol Type	G	H	J	K	t	Q
C4532 (CC1812)	2.00 ± 0.05	4.00 ± 0.10	$\varnothing 1.5 \begin{smallmatrix} +0.10 \\ 0 \end{smallmatrix}$	6.50 max.	0.60 max.	$\varnothing 1.50$ min.
C5750 (CC2220)						

* The values in the parentheses () are for reference.

Appendix 7

C0402, C0603, C1005, C1608, C2012, C3216, C3225
 (As for C3225 type, any thickness of the item except 2.5mm)
 (Material : Polystyrene)




Symbol	A	B	C	D	E	W ₁
Dimension	Ø178 ± 2.0	Ø60 ± 2.0	Ø13 ± 0.5	Ø21 ± 0.8	2.0 ± 0.5	9.0 ± 0.3

Symbol	W ₂	r
Dimension	13.0 ± 1.4	1.0

Appendix 8

C3225, C4532, C5750 (As for C3225 type, applied to 2.5mm thickness products)
 (Material : Polystyrene)




Symbol	A	B	C	D	E	W ₁
Dimension	Ø178 ± 2.0	Ø60 ± 2.0	Ø13 ± 0.5	Ø21 ± 0.8	2.0 ± 0.5	13.0 ± 0.3

Symbol	W ₂	r
Dimension	17.0 ± 1.4	1.0

Appendix 9

C1005, C1608, C2012, C3216, C3225
(As for C3225 type, any thickness of the item except 2.5mm)
(Material : Polystyrene)




Symbol	A	B	C	D	E	W
Dimension	Ø382 max. (Nominal Ø330)	Ø50 min.	Ø13 ± 0.5	Ø21 ± 0.8	2.0 ± 0.5	10.0 ± 1.5

Symbol	t	r
Dimension	2.0 ± 0.5	1.0

Appendix 10

C3225, C4532, C5750 (As for C3225 type, applied to 2.5mm thickness products)
(Material : Polystyrene)



Symbol	A	B	C	D	E	W
Dimension	Ø382 max. (Nominal Ø330)	Ø50 min.	Ø13 ± 0.5	Ø21 ± 0.8	2.0 ± 0.5	14.0 ± 1.5

Symbol	t	r
Dimension	2.0 ± 0.5	1.0

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

TDK:

C1005C0G1H180J	C5750X5R1A686M	C1005X5R1C683K	C1005X7R1E473K	C1608C0G1H050C
C1608C0G1H070D	C1608C0G1H090C	C1608C0G1H332J	C1608X5R0J106M	C1608X5R0J225K
C1608X7R1C105K	C1608X7R1C474K	C2012X5R1A335K	C2012X7R1A475K	C3216X5R0J107M
C3216X7R1C106K	C3216X7R1C106M	C3216X7R1E475K	C3225C0G1H683J	C3225X7R1C106K
C3225X7R1C156M	C3225X7R1C226M	C3225X7R1E106K	C3225X7R1H155K	C4532C0G1H104J
C1608C0G1E682J	C3225C0G1H223J	C1608C0G1E822J	C2012C0G1E153J	C1608C0G1E392J
C3225C0G1H333J	C2012C0G1E103J	C2012C0G1H122J	C1005C0G1E102J	C3225X7R1E335K
C4532X7R1E226M	C3225X7R1H335K	C3225X5R1E106M	C2012X7R1H154M	C4532X7R1H685K
C1005C0G1H330J	C1005X7R1C103K	C1608C0G1H150J	C1608C0G1H152J	C1608C0G1H270J
C3216X5R1A106M	C3225X5R1A226M	C1608X7R1H223K	C2012X7R1C225K	C1005X7R1H472K
C1005X7R1H471K	C1608X7R1H103K	C1608X7R1H104K	C1005X5R1A104K	C3225X5R1C226M
C1608C0G1H680J	C1608C0G1H681J	C4532X7R1E106M	C4532X5R1E226M	C1005C0G1H560J
C1608C0G1H101J	C1608X7R1H473K	C1608X5R1C105K	C1608C0G1H331J	C1005C0G1H390J
C4532X5R1A226M	C3225X5R0J476M	C1608X5R1A474K	C1005C0G1H680J	C1005X7R1H222K
C1005X7R1H221K	C1608X7R1E104K	C1608C0G1H330J	C3225X5R0J107M	C3216X7R1H474K
C3216X7R1H105K	C1608C0G1H271J	C1608C0G1H820J	C4532X7R1H685M	C3216X7R1H224K
C1005X5R0J224M	C1005X5R0J104K	C4532X5R0J107M	C3225X7R1E106M	C1005C0G1H470J
C3216X7R1E475M	C5750X5R1C476M	C2012C0G1H102J	C1608C0G1H100D	C1608C0G1H102J
C1608C0G1H181J	C1608C0G1H182J	C5750X7R1E226M	C1608X7R1C224K	C1005X7R1C473K
C4532X5R1A336M	C1005C0G1H181J	C1005C0G1H220J	C1005C0G1H101J	