

Chip Ferrite Bead BLM31□□□□SH1L Murata Standard Reference Specification [AEC-Q200]

1. Scope

This reference specification applies to Chip Ferrite Bead for Automotive Electronics BLM31_SH Series based on AEC-Q200.

2. Part Numbering

(1) (2)(4) (5)

(1)Product ID (4)Characteristics

(7) Category (for Automotive Electronics) (5)Typical Impedance at 100MHz (8) Numbers of Circuit

(2)Type (3)Dimension (LxW)

(6)Performance

(9)Packaging (L:Taping)

3. Rating

. Nating								
Customer Part Number	MURATA Part Number	Testing Condition) (*1) (refer to below comment)		(mA) (*2)		(Ω) ma (refer t	sistance ax. (*1) o below ment) Values After	ESD Rank 5B:12kV 6:25kV
			Турісаі	85°C	125°C		Testing	
	BLM31PG330SH1L	33±25%	33	*2 6000	*2 3500	0.009	0.018	
	BLM31PG500SH1L	35 min.	50	*2 3500	*2 2300	0.015	0.03	
	BLM31PG121SH1L	120±25%	120	*2 3500	*2 2000	0.02	0.04	6
	BLM31PG391SH1L	390±25%	390	*2 2000	*2 1250	0.05	0.10	
	BLM31PG601SH1L	600±25%	600	*2 1500	*2 1000	0.08	0.16	
	BLM31SN500SH1L	50±12.5Ω	50	*2 12000	*2 10000	0.0016	0.0021	6
	BLM31AJ601SH1L	600±25%	600	2	00	0.9	1.0	5B

[•] Operating Temperature: -55°C to +125°C

Standard Testing Conditions

< Unless otherwise specified >


Temperature: Ordinary Temp. (15 °C to 35 °C)

Humidity: Ordinary Humidity (25%(RH) to 85%(RH))

(Note) As for Rated current marked with *2, Rated Current is derated as right figure depending on the operating temperature.


< In case of doubt > Temperature: 20°C±2 °C Humidity: 60%(RH) to 70%(RH)

Atmospheric pressure: 86kPa to 106kPa



[•] Storage Temperature: -55°C to +125°C

4. Style and Dimensions



5. Marking

No marking.

6. Specifications

6-1. Electrical

No.	Item	Specification	Test Method
6-1-1	Impedance	Meet item 3.	Measuring Frequency: 100MHz±1MHz Measuring Equipment: Agilent 4291A or the equivalent Test Fixture: Agilent 16192A or the equivalent
6-1-2	DC Resistance	Meet item 3.	Measuring Equipment : Digital multi meter *Except resistance of the Substrate and Wire


6-2. Mechanical Performance (based on Table 13 for FILTER EMI SUPPRESSORS/ FILTERS) AEC-Q200 Rev.D issued June. 1 2010

	AEC	-Q200	Murata Specification / Deviation			
No.	Stress	Test Method	<u> </u>			
3	High Temperature	1000hours at 125 deg C Set for 24hours at room	Meet Table A after testing. <u>Table A</u>			
	Exposure	temperature, then	Appearance No damage			
		measured.	Impedance Change (at 100MHz) Within ±30% (for BLM31SN within±50%)			
			DC Resistance Meet item 3.			
4	Temperature Cycling	1000cycles -55 deg C to +125 deg C Set for 24hours at room temperature, then measured.	Meet Table A after testing.			
5	Destructive Physical Analysis	Per EIA469 No electrical tests	No defects			
7	Biased Humidity	1000hours at 85 deg C, 85%RH Apply max rated current.	Meet Table A after testing.			
8	Operational Life	Apply 125 deg C 1000hours Set for 24hours at room temperature, then measured	Meet Table A after testing. If the rated current of parts exceed 1A, the operating temperature should be 85 deg C.			
9	External Visual	Visual inspection	No abnormalities			
10	Physical Dimension	Meet ITEM 4 (Style and Dimensions)	No defects			

	AEC-	-Q200	M + O * T + C + C	
No	Stress	Test Method	Murata Specification / Deviation	
12	Resistance to Solvents	Per MIL-STD-202 Method 215	Not Applicable	
13	Mechanical Shock	Per MIL-STD-202 Method 213 Condition F: 1500g's(14.7N)/0.5ms/ Half sine	Meet Table B after testing. Table B Appearance No damage Impedance Change Within ±30% (at 100MHz) DC Resistance Meet item 3.	
14	Vibration	5g's(0.049N) for 20 minutes, 12cycles each of 3 orientations Test from 10-2000Hz.	Meet Table B after testing.	
15	Resistance to Soldering Heat	Solder temperature 260C+/-5 deg C Immersion time 10s	Pre-heating:150C +/-10 deg,60s to 90s Meet Table A after testing.	
17	ESD	Per AEC-Q200-002	Meet Table A after testing. ESD Rank: Refer to Item 3. Rating	
18	Solderability	Per J-STD-002	Method b : Not Applicable 95% of the terminations is to be soldered.	
19	Electrical Characterization	Measured : Impedance	No defects	
20	Flammability	Per UL-94	Not Applicable	
21	Board Flex	Epoxy-PCB(1.6mm) Deflection 2mm(min) 60s minimum holding time	Meet Table B after testing.	
22	Terminal Strength	Per AEC-Q200-006	No defects	
30	Electrical Transient Conduction	Per ISO-7637-2	Not Applicable	

7. Specification of Packaging

7-1. Appearance and Dimensions (8mm-wide plastic tape)



*Dimension of the Cavity is measured at the bottom side.

(in mm)

- (1) Taping
 - Products shall be packaged in the each embossed cavity of 8mm-wide, 4mm-pitch and plastic tape continuously and sealed by cover tape.
- (2) Sprocket hole: Sprocket hole shall be located on the left hand side toward the direction of feed.
- (3) Spliced point: The cover tape has no spliced point.
- (4) Missing components number

Missing components number within 0.1% of the number per reel or 1 pc., whichever is greater, and are not continuous. The specified quantity per reel is kept.


7-2. Tape Strength

(1) Pull Strength

Plastic tape	5N min.
Cover tape	10N min.

(2) Peeling off force of Cover tape

0.2N to 0.7N (Minimum value is typical.) *Speed of Peeling off:300mm/min



7-3. Taping Condition

(1) Standard quantity per reel

Quantity per 180mm reel: 3000 pcs. / reel

- (2) There shall be leader-tape (cover tape only and empty tape) and trailer- tape (empty tape) as follows.
- (3) Marking for reel

The following items shall be marked on a label and the label is stuck on the reel.

(Customer part number, MURATA part number, Inspection number (*1), RoHS marking (*2), Quantity, etc)

*1) « Expression of Inspection No. »

 $\begin{array}{c|c} \square \square & OOOO & \times \times \times \\ \hline (1) & (2) & (3) \end{array}$

(1) Factory Code

(2) Date

First digit : Year / Last digit of year

Second digit

: Month / Jan. to Sep. \rightarrow 1 to 9, Oct. to Dec. \rightarrow O, N, D

Third, Fourth digit: Day

(3) Serial No.

*2) « Expression of RoHS marking »


ROHS $-\frac{Y}{(1)}(\underline{\Delta})$

- (1) RoHS regulation conformity parts.
- (2) MURATĂ classification number
- (4) Outside package

These reels shall be packed in the corrugated cardboard package and the following items shall be marked on a label and the label is stuck on the box.


(Customer name, Purchasing order number, Customer part number, MURATA part number, RoHS marking (*2), Quantity, etc)

(5) Dimensions of reel and taping (leader-tape, trailer-tape)





7-4. Specification of Outer Case



Outer Case Dimensions (mm)		nsions	Standard Reel Quantity in Outer Case (Reel)
W	D	Н	(Reei)
186	186	93	5

^{*} Above Outer Case size is typical. It depends on a quantity of an order.

8. / Caution

8-1. Rating

Do not use products beyond the Operating Temperature Range and Rated Current.

8-2. Surge current

Excessive surge current (pulse current or rush current) than specified rated current applied to the product may cause a critical failure, such as an open circuit, burnout caused by excessive temperature rise. Please contact us in advance in case of applying the surge current.

8-3. Fail Safe

Be sure to provide an appropriate fail-safe function on your product to prevent from a second damage that may be caused by the abnormal function or the failure of our products.

8-4. Limitation of Applications

Please contact us before using our products for the applications listed below which require especially high reliability for the prevention of defects which might directly cause damage to the third party's life, body or property.

(1)Aircraft equipment (6)Disaster prevention / crime prevention equipment

(2)Aerospace equipment (7)Traffic signal equipment

(3)Undersea equipment (8)Transportation equipment (trains, ships, etc.)

(4)Power plant control equipment (9)Applications of similar complexity and /or reliability requirements

(5)Medical equipment to the applications listed in the above

9. Notice


This product is designed for solder mounting.

Please consult us in advance for applying other mounting method such as conductive adhesive.


9-1. Land pattern designing

• Standard land dimensions (Flow and Reflow soldering)

< BLM31AJ type >



< BLM31PG/31SN type >




Туре	Rated Current		and pad thickness and dimension a		
	(A)	18µm	35µm	70µm	
	1.5/2	1.2	1.2	1.2	
BLM31PG	3.5	2.4	1.2	1.2	
	6	6.4	3.3	1.65	
BLM31SN	10~12	ı	9.8	4.9	

(in mm)

^{*}The excessive heat by land pads may cause deterioration at joint of products with substrate.

• Land dimensions on Flow soldering for 2.5mm pitch mounting



*As for BLM31PG type, taking land pad thickness and rated current into account.

а	b	С	d	е	
2.0	4.2 to 5.2	1.2	1.3	1.35	
				(in	mm)

*The pattern shall be designed to above drawing to prevent causing the solder bridge when products are mounted by 2.5mm pitch flow soldering.

9-2. Soldering Conditions

Products can be applied to reflow and flow soldering.

(1) Flux, Solder

Flux	Use rosin-based flux, but not highly acidic flux (with chlorine content exceeding 0.2(wt)%.)
	Do not use water-soluble flux.
Solder	Use Sn-3.0Ag-0.5Cu solder
	Standard thickness of solder paste : 100 μm to 200 μm

(2) Soldering conditions


• Pre-heating should be in such a way that the temperature difference between solder and ferrite surface is limited to 150°C max. Also cooling into solvent after soldering should be in such a way that the temperature difference is limited to 100°C max.

Insufficient pre-heating may cause cracks on the ferrite, resulting in the deterioration of product quality.

Standard soldering profile and the limit soldering profile is as follows.
 The excessive limit soldering conditions may cause leaching of the electrode and / or resulting in the deterioration of product quality.


(3) soldering profile

☐Flow soldering profile



	Standard Profile	Limit Profile
Pre-heating	150°C、60s min.	
Heating	250°C、4∼6s	265°C±3°C, 5s max.
Cycle of flow	2 times	2 times

□Reflow soldering profile



	Standard Profile	Limit Profile
Pre-heating	150~180°C 、90s±30s	
Heating	above 220°C、30s~60s	above 230°C、60s max.
Peak temperature	245±3°C	260°C, 10s
Cycle of reflow	2 times	2 times


9-3. Reworking with soldering iron

- Pre-heating: 150°C, 1 min
- Tip temperature: 350°C max.
- Soldering time: 3 (+1, -0) seconds.
- Soldering iron output: 80W max.
- Tip diameter: φ 3mm max.
- Times : 2times max.

Note: Do not directly touch the products with the tip of the soldering iron in order to prevent the crack on the ferrite material due to the thermal shock.

9-4. Solder Volume

Solder shall be used not to be exceed as shown below.




Accordingly increasing the solder volume, the mechanical stress to product is also increased. Exceeding solder volume may cause the failure of mechanical or electrical performance.

9-5. Attention regarding P.C.B. bending


The following shall be considered when designing and laying out P.C.B.'s.

(1) P.C.B. shall be designed so that products are not subject to the mechanical stress for board warpage. <Products direction>



Products shall be located in the sideways direction (Length: a<b) to the mechanical stress.

(2) Products location on P.C.B. separation. Products (A, B, C, D) shall be located carefully so that products are not subject to the mechanical stress due to warping the board. Because they may be subjected the mechanical stress in order of $A>C>B \cong D$.



9-6. Mounting density

Add special attention to radiating heat of products when mounting the inductor near the products with heating. The excessive heat by other products may cause deterioration at joint of this product with substrate.



9-7. Operating Environment

Do not use this product under the following environmental conditions, on deterioration of the Insulation Resistance of the Ferrite material and/or corrosion of Inner Electrode may result from the use.

- (1) in the corrodible atmosphere (acidic gases, alkaline gases, chlorine, sulfur gases, organic gases and etc.)
- (2) in the atmosphere where liquid such as organic solvent, may splash on the products.
- (3) in the atmosphere where the temperature / humidity changes rapidly and it is easy to dew.

9-8. Resin coating

The impedance value may change and/or it may affect on the product's performance due to high cure-stress of resin to be used for coating / molding products. So please pay your careful attention when you select resin. In prior to use, please make the reliability evaluation with the product mounted in your application set.

9-9. Cleaning Conditions

Products shall be cleaned on the following conditions.

- (1) Cleaning temperature shall be limited to 60°C max. (40°C max. for IPA.)
- (2) Ultrasonic cleaning shall comply with the following conditions, avoiding the resonance phenomenon at the mounted products and P.C.B.

Power:20W/ℓ max. Frequency:28kHz to 40kHz Time:5 min max.

- (3) Cleaner
 - 1.Alternative cleaner
 - Isopropyl alcohol (IPA)
 - 2. Aqueous agent
 - •PINE ALPHA ST-100S
- (4) There shall be no residual flux and residual cleaner after cleaning.

In the case of using aqueous agent, products shall be dried completely after rinse with de-ionized water in order to remove the cleaner.

(5) Other cleaning


Please contact us.

9-10. Handling of a substrate

After mounting products on a substrate, do not apply any stress to the product caused by bending or twisting to the substrate when cropping the substrate, inserting and removing a connector from the substrate or tightening screw to the substrate.

Excessive mechanical stress may cause cracking in the product.

Bending



Twisting



9-11. Storage Conditions

(1) Storage period

Use the products within 6 months after delivered.

Solderability should be checked if this period is exceeded.

- (2) Storage conditions
 - Products should be stored in the warehouse on the following conditions.

Temperature: -10°C to 40°C

Humidity : 15% to 85% relative humidity

No rapid change on temperature and humidity

- Don't keep products in corrosive gases such as sulfur, chlorine gas or acid, or it may cause oxidization of electrode, resulting in poor solderability.
- Products should be stored on the palette for the prevention of the influence from humidity, dust and so on.
- Products should be stored in the warehouse without heat shock, vibration, direct sunlight and so on.
- Products should be stored under the airtight packaged condition.
- (3) Delivery

Care should be taken when transporting or handling product to avoid excessive vibration or mechanical shock.

10 . 🔬 Note

- (1)Please make sure that your product has been evaluated in view of your specifications with our product being mounted to your product.
- (2)You are requested not to use our product deviating from the agreed specifications.
- (3)The contents of this reference specification are subject to change without advance notice. Please approve our product specifications or transact the approval sheet for product specifications before ordering.