E/H (Ta2N) (Military M/D55342)

Vishay Dale Thin Film






www.vishay.com

Thin Film MIL chip resistors feature an all sputtered wraparound termination for excellent adhesion and dimensional uniformity. They are ideal in applications requiring stringent performance requirements. Established reliability is assured through 100 % screening and extensive environmental lot testing.

CONSTRUCTION



FEATURES

- Established reliability, "R" and "U" failure rate level (0.01 % per 1000 h), C = 2
- High purity alumina substrate
- Wraparound termination featuring a tenacious adhesion layer covered with an electroplated nickel barrier layer for +150 °C operating conditions
- Very low noise and voltage coefficient (< -25 dB, 0.5 ppm/V)
- Non-inductive
- Laser-trimmed tolerances \pm 0.1 %
- Complete MIL-testing available in-house
- · Antistatic waffle pack or tape and reel packaging available
- Military / aerospace / QPL approval

TYPICAL PERFORMANCE

	ABSOLUTE
TCR	25
TOL.	0.1

STANDARD ELECTRICAL SPECIFICATIONS										
TEST	SPECIFICATIONS	CONDITIONS								
Material	Tantalum nitride (Ta ₂ N) resistor film	-								
Resistance Range	49.9 Ω to 3.3 MΩ	-								
TCR: Absolute	± 25 ppm/°C to ± 300 ppm/°C	-55 °C to +125 °C								
Tolerance: Absolute	± 0.1 % to ± 10 %	+25 °C								
Stability: Absolute	$\Delta R \pm 0.02 \%$	2000 h at +70 °C								
Stability: Ratio	-	-								
Voltage Coefficient	0.1 ppm/V	-								
Working Voltage	30 V to 200 V	-								
Operating Temperature Range	-55 °C to +150 °C	-								
Storage Temperature Range	-55 °C to +150 °C	-								
Noise	< - 25 dB	-								
Shelf Life Stability: Absolute	Δ <i>R</i> ± 0.01 %	1 year at +25 °C								

COMPONENT RATINGS

	POWER	WORKING	RESIST	TANCE RANGE BY TOLER	ANCE		
CASE SIZE	RATING (mW)	VOLTAGE (V)	0.1 %, 0.25 %, 0.5 %, 1 %	2.0 % and 5.0 %	10 %		
M55342/01	50	40	49.9 Ω to 64.9 kΩ	51 Ω to 68 k Ω	51 Ω to 68 k Ω		
M55342/02	125	40	49.9 Ω to 140 kΩ	51 Ω to 150 k Ω	51 Ω to 150 k Ω		
M55342/03	200	75	49.9 Ω to 357 kΩ	51 Ω to 360 k Ω	51 Ω to 360 k Ω		
M55342/04	150	125	49.9 Ω to 806 kΩ	51 Ω to 820 k Ω	51 Ω to 820 k Ω		
M55342/05	225	175	49.9 Ω to 1.5 MΩ	51 Ω to 1.5 M Ω	51 Ω to 1.5 MΩ		
M55342/06	150	50	49.9 Ω to 309 kΩ	51 Ω to 820 k Ω	51 Ω to 820 k Ω		
D55342/07	250	100	49.9 Ω to 1 MΩ	51 Ω to 1 M Ω	51 Ω to 1 M Ω		
M55342/08	800	150	49.9 Ω to 2.0 MΩ	49.9 Ω to 2.0 M Ω	51 Ω to 2.23 MΩ		
M55342/09	1000	200	49.9 Ω to 3.01 MΩ	51 Ω to 3 M Ω	51 Ω to 3.3 MΩ		
M55342/10	500	75	49.9 Ω to 604 kΩ	51 Ω to 620 kΩ	51 Ω to 680 kΩ		
M55342/11	50	30	49.9 Ω to 49.9 kΩ	51 Ω to 51 k Ω	51 Ω to 51 kΩ		
M55342/12	100	50	49.9 Ω to 130 kΩ	51 Ω to130 kΩ	51 Ω to 150 kΩ		

Note

• Values listed are a guide, refer to MIL spec for value/tolerance allowance

Revision: 15-Sep-16




www.vishay.com

E/H (Ta2N) (Military M/D55342)

Vishay Dale Thin Film

DIMENSIONS in inches



CASE SIZE	TERM.	L	w	т	D	E
M55342/01	В	0.055 ± 0.006	0.025 ± 0.005	0.010 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/02	В	0.055 ± 0.006	0.050 ± 0.005	0.010 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/03	В	0.105 ± 0.007	0.050 ± 0.005	0.010 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/04	В	0.155 ± 0.007	0.050 ± 0.005	0.015 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/05	В	0.230 ± 0.007	0.075 ± 0.005	0.010 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/06	В	0.080 ± 0.006	0.050 ± 0.005	0.010 to 0.033	0.016 ± 0.008	0.015 ± 0.005
D55342/07	В	0.126 ± 0.008	0.063 ± 0.005	0.010 to 0.033	0.020 + 0.005/- 0.010	0.020 + 0.005/- 0.010
M55342/08	В	0.209 + 0.009/- 0.018	0.098 ± 0.005	0.010 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/09	В	0.259 + 0.009/- 0.015	0.124 ± 0.005	0.010 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/10	В	0.105 ± 0.007	0.100 ± 0.005	0.010 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/11	В	0.040 ± 0.005	0.025 ± 0.005	0.010 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/12	В	0.064 ± 0.006	0.032 ± 0.005	0.010 to 0.033	0.012 ± 0.005	0.015 ± 0.005

ENVIRONMENTAL TESTS												
ENVIRONMENTAL TEST	MIL-PRF-55342 LIMITS (ΔR ±)	VISHAY PERFORMANCE (ΔR ±)										
Thermal Shock	0.1 %	0.020 %										
Low Temperature Operation	0.1 %	0.025 %										
Short Time Overload	0.1 %	0.050 %										
High Temperature Exposure	0.1 %	0.009 %										
Resistance to Bonding	0.2 %	0.006 %										
Moisture Resistance	0.2 %	0.004 %										
TCR	± 25 ppm/°C	< 15 ppm/°C										
Life (2000 h at + 70 °C)	0.5 %	0.02 %										
Life (10 000 h at + 70 °C)	2.0 %	0.04 %										

MECHANICAL SPECIFICATIONS									
Resistive Element	Tantalum nitride (Ta ₂ N)								
Substrate Material	Alumina								
Chip Terminations	Solder over nickel								
Plated Solder	90/10								

FSCM CAGE # - 57489

2


Document Number: 60120



E/H (Ta2N) (Military M/D55342)

Vishay Dale Thin Film

DERATING



GLOBAL PART NUMBER INFORMATION																										
New	Glo	obal	Pa	rt N	umbe	ring	g: M	5534	2E()6B9	BOON	IT1:	2													
	М		5		5	3		4		2	Ε		0	6		В		9	В	}	0 ()	М		T 1	4
				Г							_													Г		
GLOB MODE		СН		TCR CTE	RISTIC		C/ SI	SE ZE	т	ERM	INATI	NC		(ЭНМ	IIC V	ALUE	Ξ			FAILURE RATE		PAC	ЖA	GING	THIN FILM CODE
M553 or							B = solderable				Three digits and a letter. Letter $M = 1.0$ % per 1000							ber 1000 h	Standard Packaging: BS = BULK				4 for			
D553 4 (/07 si	55342 K = 100 ppm/°C 03 = 1005							multiplier and decimal locator.							p	P = 0.1 % per 1000 h	100 min., 1 mult WS =WAFFLE			Ta ₂ N resistor film						
only)	M = 300 ppm/°C 05 = 2208 06 = 0705											e 1Ω 1kΩ 1ΜΩ			l I	R = 0.01 % per 1000 h J = 0.01 %	100 min., 1 mult TAPE AND REEL		EL	type					
	07 = 1206 08 = 2010									0.25 % R U V per 1000 h TI = 10				T0 = 100 min., 100 mult T1 = 1000 min., 1000 mult												
							10 =	2512 1010						50 % 1 %		W D	Y E		Z F			T5 =	500 r	nin.	., 300 mult ., 500 mult	
								0402 0603						2 %		G	Н		Т			5K depend		der		
														5 % 0 %		J M	K N		L P			docu	ment	t 60		
																				ial Pa		., 1 mult aging:				
																						(item	single	e lot	., 1 mult t date code)	
																						(pack	age u	unit	., 1 mult single lot	
																						date (TAPE	AND	RE		
																						(item	single	e lot	., 1 mult t date code) ., 1 mult	
																							age u	unit	single lot	



Vishay

Disclaimer

ALL PRODUCT, PRODUCT SPECIFICATIONS AND DATA ARE SUBJECT TO CHANGE WITHOUT NOTICE TO IMPROVE RELIABILITY, FUNCTION OR DESIGN OR OTHERWISE.

Vishay Intertechnology, Inc., its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "Vishay"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained in any datasheet or in any other disclosure relating to any product.

Vishay makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Vishay disclaims (i) any and all liability arising out of the application or use of any product, (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability.

Statements regarding the suitability of products for certain types of applications are based on Vishay's knowledge of typical requirements that are often placed on Vishay products in generic applications. Such statements are not binding statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application. Parameters provided in datasheets and / or specifications may vary in different applications and performance may vary over time. All operating parameters, including typical parameters, must be validated for each customer application by the customer's technical experts. Product specifications do not expand or otherwise modify Vishay's terms and conditions of purchase, including but not limited to the warranty expressed therein.

Except as expressly indicated in writing, Vishay products are not designed for use in medical, life-saving, or life-sustaining applications or for any other application in which the failure of the Vishay product could result in personal injury or death. Customers using or selling Vishay products not expressly indicated for use in such applications do so at their own risk. Please contact authorized Vishay personnel to obtain written terms and conditions regarding products designed for such applications.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of Vishay. Product names and markings noted herein may be trademarks of their respective owners.