




Highest power rating with long life – Standard parts stocked*

APPLICATIONS

Wearable electronic & IoT devices – Memory backup circuits

Nominal Voltage	3.7VDC (4.2VDC to 3.0VDC)				
Operating Temperature Range	-20°C to +60°C				
Storage Temperature Range	-20°C to +60°C (one month) -20°C to +40°C (up to 3 months) -20°C to +25°C (up to 1 year)				
Storogo Consoitu	Nominal	See part listing 0.2C rate, 3.0V cut-off			
Storage Capacity	Minimum	See part listing 0.2C rate, 3.0V cut-off			
Charging Voltage	4.2VDC <u>+</u> 0.03V				
Charging current	0.5CA				
Charging Time		< 3.0 hours			
Charging method		Constant Current/ Constant Voltage (CCCV)			
Discharge Company	Standard	0.2CA			
Discharge Current	Maximum	2CA			
Discharge Cut-off Voltage	3.0V				
Anode	Graphite				
Cathode	Lithium nickel manganese cobalt oxide				
Certification	UL1642 – MH28281 UL2054 – MH45944				

Markings





Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com





Standard Coin Cell Options

IC Part	(mAh) Charging C		Curr	Discharge Max Current Int (mA) Res		Weight (G)	Maximum Diameter	Height (mm)	
Number	Nom.	Min.	(mA)	STD	MAX	(mΩ)	(0)	(mm)	(1111)
RJD2032C1	85	80	40	17	170	600	3.4	20	3.5
RJD2048	120	110	60	24	240	700	4.2	20.	5.0
RJD2430C1	110	104	55	22	220	500	4.5	24.5	3.15
RJD2440	150	140	75	30	300	700	5.4	24.5	4.3
RJD2450	200	190	100	40	400	500	6.5	24.5	5.4
RJD3032	200	190	100	40	400	600	7.2	30	3.4
RJD3048	300	290	150	60	600	400	9.3	30	4.8
RJD3555	500	490	250	100	1000	200	14	35.2	5.7

Standard PCM & Connector Options

IC Part	-	acity Ah)	Charging Current	Disch Curi	rent	Maximum Internal	Weight	Maximum Diameter	Height
Number	Nom.	Min.	(mA)	(m	· '	Resistance	(G)	(mm)	(mm)
				STD	MAX	(mΩ)			
RJD3032HPPV30M	200	190	100	40	400	600	7.2	30	3.4
RJD3048HPPV30M	300	290	150	60	600	400	9.3	30	4.8
RJD3555HPPV30M	500	490	250	100	1000	200	14	35.2	5.7

Standard Leaded Options

IC Part	-	acity Ah)	Charging Current	harging Current Internal			Weight	Maximum Diameter	Height
Number	Nom.	Min.	(mA)	STD	MAX	(mΩ)	(G)	(mm)	(mm)
RJD2032C1ST1	85	80	40	17	170	600	3.4	20	3.5
RJD2048ST1	120	110	60	24	240	700	4.2	20.	5.0
RJD2430C1ST1	110	104	55	22	220	500	4.5	24.5	3.15
RJD2440ST1	150	140	75	30	300	700	5.4	24.5	4.3
RJD2450ST1	200	190	100	40	400	500	6.5	24.5	5.4
RJD3032ST1	200	190	100	40	400	600	7.2	30	3.4
RJD3048ST1	300	290	150	60	600	400	9.3	30	4.8
RJD3555ST1	500	490	250	100	1000	200	14	35.2	5.7



Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com



Cell Dimensions

IC		Fres	Cycled cell (after 500 cycles)				
Part	Shipping	(Charged)	Full C	harge	Full Charge		
Number	Maximum Diameter (mm)	Maximum Height (mm)	Maximum Diameter (mm)	Maximum Height (mm)	Maximum Diameter (mm)	Maximum Height (mm)	
RJD2032C1*	20	3.5	20	3.6	20	3.7	
RJD2048*	20	5	20	5.2	20	5.3	
RJD2430C1*	24.5	3.15	24.5	3.25	24.5	3.3	
RJD2440*	24.5	4.3	24.5	4.4	24.5	4.5	
RJD2450*	24.5	5.4	24.5	5.5	24.5	5.6	
RJD3032*	30	3.4	30	3.5	30	3.6	
RJD3048*	30	4.8	30	4.9	30	5.2	
RJD3555*	35.2	5.7	35.2	5.8	35.2	5.9	


*Same cell dimensions for PCM and leaded options

Part Numbering

RJD 2032C1	А	В	С	D	E
Section 1	Section 2	Section 3	Section 4	Section 5	Section 6

Section 1 – IC standard part number (Bare cell)


Section 2 – Termination style



Termination Styles

Vour Global Source for World-Class Capacitors © 2016 Illinois Capacitor

North America Tel: 847.675.1760 sales@illcap.com




Your Global Source for World-Class Capacitors

North America Tel: 847.675.1760 sales@illcap.com







Contact IC if other termination type is preferred

Section 3 – Connector supplied with PCM indicator

Connector with	Connector without
PCM	PCM
Р	N

Section 4 - Wire gauge. 30 gauge (code V) standard.

AWG	Code	AWG	Code	AWG	Code	AWG	Code	AWG	Code	AWG	Code
12	Α	16	E	20	J	24	N	28	Т	32	Х
13	В	17	F	21	K	25	Р	29	U	33	Y
14	С	18	G	22	L	26	Q	30	V	34	Z
15	D	19	Н	23	М	27	R	31	W	35	0
Contact	IC if oth	er wire o	ai anuar	desired							

Contact IC if other wire gauge is desired.

Section 5 – Lead Length (types SW and HP). Specify lead length in mm.

Section 6 – Connector option (types SW and HP)


Your Global Source for World-Class Capacitors

© 2016 Illinois Capacitor

North America Tel: 847.675.1760 sales@illcap.com



Connector types



HP lead style are supplied with a PCM (Protection Circuit Module). PCM Type: Powerlogics part # RJD 201 or RJD 9901 (see Protection Circuit Module section below for complete specifications).

PCM option

Protection Circuit Module

(Only for HP lead style)

Specification	RJD 9901	RJD 201
PCM used with indicated corresponding bare cell part number	RJD3032 RJD3048 RJD3555	RJD2032C1, RJD2048, RJD2430C1, RJD2440, RJD2450
Main IC	SP31ABE	MP29A
PCB	SALTEK, APEX	SALTEK, APEX
FET	Х	Х
PTC	MicroSMD175F-2 (TE)	х
L terminal	Х	Х
Capacitor	2Point	2Point
Resistor	2Point	1Point
Dimension(L*W*T)	16.9*3.9*2.0mm	11.0X3.5X1.75mm
Wake-up Function	NO	NO
Overcharge Detection Voltage	4.275V ± 25mV	4.25V~4.3V
Overcharge Detection Delay Time	700.0mSec ~ 1300mSec	800.0mSec ~ 1200mSec
Over-Discharge Detection Voltage	2.242V~2.358V	2.76V~2.84V
Over-Discharge Detection Delay Time	14.0mSec~26.0mSec	16.0mSec~24.0mSec



Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com





Over-Discharge Current Detection	1.2 ~ 4.0A	0.77 ~ 1.76A
Overcharge Current Detection	0.9A ~ 4.4A	0.9A ~ 4.4A
Over-Discharge Current Protection Delay Time	8.0mSec ~ 16.0mSec	4.8mSec ~ 7.2mSec
Short Detection Delay Time	100µs ~ 500µs	280µs ~ 560µs
PCM Impedance	< 220mΩ	< 46mΩ
Operation Current Consumption	Max 6.0µA(TYP 4.0µA)	Max 6.0µA(TYP 3.0µA)
Power-Down Mode Current Consumption	Max 0.1µA	Max 0.1µA
Distance Between B+, B- Tab	13.93mm	5.25mm

Battery Operation Instruction:

Charging

a. Charge the battery in a temperature range of 0°C to + 45°C.

b. Charge the battery at a constant current of 0.5C until 4.20VDC±0.03VDC per cell is attained. Charge rates greater than 1C are NOT recommended. (C: Rated Capacity of Battery)

- c. Maintain charge voltage at 4.20VDC per cell for 3.0 hours (recommended for maximum capacity).
- * Use a constant current, constant voltage (CC/CV) lithium-ion (Li+) battery charge controller.

* Do not continue to charge battery over specified time.

Discharging

- a. Recommended cut-off voltage to 3.0VDC. Recommended maximum discharge rate is 2C at constant current.
- b. For maximum performance, discharge the battery in a temperature range of -20° C to $+45^{\circ}$ C.

Protection Circuit

Protection circuit can be provided upon request. However, protection circuit may be omitted for most applications without damaging performance and safety. Please consult our engineering staff for technical advice.

Storage Recommendations

Storage Temperature and Humidity

Store the battery within a temperature range of -20°C to +45°C, low humidity, non-corrosive gas atmosphere and no condensation on the battery.

Long Period Storage

In case of a long storage period (more than 3 months), store the battery within a temperature range of –20°C to +25°C, low humidity and non-corrosive gas atmosphere.

Standard Test Conditions

Unless otherwise specified, all tests are conducted at $25^{\circ}C \pm 3^{\circ}C$ and relative humidity of $65\% \pm 20\%$.



Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com





Electrical Characteristics

Standard Charge and Discharge Conditions

- A. The "Standard Charge" means charging the Cell with initial charge current (0.5C) and with a constant voltage of 4.2VDC (<u>+</u> 0.03VDC) and the specified cut-off current (see table 1) at 25°C for 3 hours.
- B. Standard discharge means discharging cell with constant discharge current (0.2C)(see table 1) and with 3.0VDC cut-off voltage at 25°C
- C. Initial Discharge Capacity
- D. The initial capacity measured under the standard test conditions
- E. Initial Discharge Capacity: See standard part listing
- F. Initial Internal resistance: see standard part listing
- G. Internal resistance measured at 1 kHz after Standard Charge.
- H. Cycle Life (500 cycles): See table 1
- I. Temperature dependence of discharge capacity. See discharge table.
- J. Relative capacity at each temperature measured with a constant discharge current (0.2C) with 3.0VDC cutoff after the standard charge shown below.

IC Part	Discharge Temperature							
Number	-20°C	-10°C	25°C	60°C				
RJD2032C1	>60 %	>80%	100 %	>95%				
RJD2048	>60 %	>80%	100 %	>80%				
RJD2430C1	>60 %	>80%	100 %	>95%				
RJD2440	>60 %	>80%	100 %	>80%				
RJD2450	>60 %	>80%	100 %	>80%				
RJD3032	>60 %	>80%	100 %	>80%				
RJD3048	>60 %	>80%	100 %	>80%				
RJD3555	>60 %	>80%	100 %	>80%				

Discharge Table

Т	้ล	b	le	1
	u	~		

IC Part Number	Charging Current (0.5C) (mA)	Constant Discharge Current (0.2C) (mA)	Charging end condition (at CV mode) (mA)	Capacity after 500 cycles (mAh)
RJD2032C1	40	16	2.4	56
RJD2048	60	24	3.6	77
RJD2430C1	55	22	3.3	72.8
RJD2440	75	30	4.5	98
RJD2450	100	40	6	133
RJD3032	100	40	6	133
RJD3048	150	60	9	203
RJD3555	250	100	15	350

Vour Global Source for World-Class Capacitors

North America Tel: 847.675.1760 sales@illcap.com



Discharge Characteristics on Current Load (C-Rate)

Relative capacity at each load, measured with constant discharge current 0.2C, 0.5C, 1.0C, 2C with 3.0VDC cut-off after Standard Charge shown below.

Charge Current	Discharge Current			
Standard Charge	0.2 CA	0.5 CA	1 CA	2.0 CA
	100 %	> 95 %	> 90 %	> 50%

Shipment

The Cell shall be shipped with 30% of the nominal voltage. (Nominal Cell voltage range: $3.7 \sim 3.8$ V). 30% SOC is only for air transport.

Storage Characteristics

After storage at the conditions listed below, the battery is measured at the standard charge and discharge conditions stated under the electrical characteristics.

Storage Condition	Charge State	Capacity Retention	Capacity Recovery
20 days at 60°C	Shipping charge	-	> 85%
20 days at 60°C	Full charge	> 70%	> 85%
60 days at 60°C	Full charge	> 40%	> 60%
30 days at 60°C, 90%RH	Full charge	> 40%	> 70%

Safety Test

Test	Test Method	Criteria
High Temperature	Storing a cell at 90°C for 4 hours after being charged to 4.2VDC	No leakage
High Temperature and High Humidity	Storing a cell at 60°C and 90% RH for 1 week after being charged to 4.2VDC	No leakage
Thermal Shock Test	Store a fully charged cell (4.2VDC) at 60°C for 2 hours then at -20°C for 2 hours. 10 cycles with a maximum transition time of 5 minutes.	No leakage
Hot Box Test	A cell is to be heated in a gravity convection oven. The temperature of the oven is to be raised 5°C+/- 2°C per minute to a temperature of 130°C and remain at that temperature for 10 minutes	No explosion, No fire
Overcharge Test	Charge the test samples with constant current (3C) and voltage 4.5VDC. Test samples remain on test for 2.5 hours	No explosion, No fire
Impact Test	A test cell is to be placed on a flat surface. The bar of 9.1 kg weight and 15.8 mm diameter is dropped from a height of 610 mm onto the cell.	No explosion, No fire



Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com





Short-Circuit Test	A cell is to be short-circuited by connecting the positive and negative terminals of the battery with copper wire having a maximum resistance load of $100m\Omega$.	No fire or explosion, until battery is completely discharged
Nail Test	A stainless steel nail having a diameter of 4.0 mm is punched through the cell until the nail has passed through the opposite side of the cell.	No explosion, No fire
Applying Pressure	Placing pressure on entire surface of a fully charged cell with 7kg for 72 hours	No leakage, No weight decrease

Precautions and Safety Instructions

Lithium-Ion rechargeable batteries subjected to abusive conditions can become damaged and/or cause personal injury. Please read and observe the standard battery precautions below before using.

Note 1. The customer is required to contact Illinois Capacitor in advance, if and when the customer needs other applications or operating conditions other than those described in this document.

Note 2. Illinois Capacitor will take no responsibility for any accident where the cell is used under other conditions than those described in this document.

Precautions and Safety Instructions:

- a. Do not expose the battery to extreme heat or flame.
- b. Do not short circuit, over-charge or over-discharge the battery.
- c. Do not subject the battery to strong mechanical shocks.
- d. Do not immerse the battery in water or sea water, or get it wet.
- e. Do not reverse the polarity of the battery for any reason.
- f. Do not disassemble or modify the battery.
- g. Do not remove charge/discharge protection circuitry.
- h. Do not handle or store with metallic objects like necklaces, coins or hairpins, etc.
- i. Do not use the battery if possible damage or deformation is present.
- j. Do not connect battery to the plug socket or car-cigarette-plug.
- k. Do not directly solder onto the battery. Only spot weld lead onto battery. Soldering iron temperature should be limited to 350°C with a soldering time of <5 seconds.
- I. Do not place batteries in a solder bath.
- m. Do not touch a leaked battery directly.
- n. Do not use for other equipment.
- o. Do not mix Lithium-ion batteries.
- p. Do not use or leave the battery in direct sunlight (or in heated car by sunshine).
- q. Keep battery away from children.
- r. Use only the specified charger and observe charging requirement.
- s. Do not drive a nail into battery or strike battery with another battery or insert a screw into the battery
- t. Do not smash or throw battery.
- u. Recharge the battery every 6 months.
- v. Follow recommended charging conditions when charging battery.

Warnings:

- a. Do not swallow. Keep out of reach of infants and children. If swallowed call physician immediately.
- b. Do not put battery in microwave or pressure cooker.
- c. Do not use battery together with a primary battery, such as dry battery types or batteries with different capacities.



Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com



- d. Do not replace battery with a different type or model.
- e. Discontinue use of battery if an unusual odor, discoloration, deformation, internal heating or other unusual characteristic changes are detected.
- f. Do not have any leaked electrolyte come in contact with eyes. If contact occurs flush eyes immediately with water and consult a doctor.
- g. If charging does not stop after expected charging time, stop charging battery.

Requirement for Safety Assurance

For safety assurance, please discuss the equipment design, its system and protection circuit of Lithium-ion battery with Illinois capacitor in advance.

Consult with Illinois Capacitor about high rate current, rapid charge and special application.



Your Global Source for World-Class Capacitors © 2016 Illinois Capacitor North America Tel: 847.675.1760 sales@illcap.com

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Cornell Dubilier:

 RJD3032HPPV30M
 RJD2032C1
 RJD3048HPPV30M
 RJD3048
 RJD2430C1
 RJD2450
 RJD2440
 RJD3555

 RJD2048
 RJD3555HPPV30M
 RJD3032
 RJD2430C1
 RJD2450
 RJD2440
 RJD3555